

FILTER CARTRIDGE AND PROCESS FOR PRODUCING THE SAME

FIELD OF THE INVENTION

5 The present invention relates to a filter cartridge and a process for producing the same, specifically to a cylindrical filter cartridge which is prepared by winding a non-woven fabric strip comprising thermoplastic fibers on a perforated cylinder in a twill form and which is excellent in a liquid-passing property, a filter life and stability of a filtering accuracy, and a process for producing the same.

BACKGROUND OF THE INVENTION

10 Various filters for clarifying a fluid are presently developed and produced. Among them, cartridge-type filters (hereinafter called filter cartridges) are widely used in the industrial field, for example, for removing suspended particles in industrial liquid materials, removing cakes flowing out of a cake filtering apparatus and clarifying industrial water.

15 Several kinds of structures of a filter cartridge have so far been proposed. The most typical one is a bobbin winder-type filter cartridge, which is a cylindrical filter cartridge prepared by winding a spun yarn as a filter material on a perforated cylindrical core in a twill form and then fluffing the spun yarn. This type has long been used due to inexpensiveness and easiness in production.

Another type of structure includes a non-woven fabric-laminated type filter cartridge. This is a cylindrical filter cartridge prepared by winding several kinds of non-woven fabrics such as a carding non-woven fabric stepwise and concentrically on a perforated cylindrical core. A recent advanced technique in a non-woven fabric production has allowed some of them to be put to practical use.

However, the above-mentioned filter cartridges have several defects. For example, in the bobbin winder-type filter cartridge for trapping foreign matters by means of fluffs of fluffed spun yarns and also in gaps of the spun yarns, it is difficult to control the size and form of the fluffs and gaps. This limits size and amount of the foreign matters that can be trapped. Further, constitutional fibers of a spun yarn, which is made from short fibers, fall away when fluid flows onto the filter cartridge.

Furthermore, in producing a spun yarn, a trace amount of a surfactant is often applied onto a surface of material short fibers to prevent the short fibers from sticking to a spinning machine by electrostatic charge or the like. Filtering a liquid by means of a filter cartridge using surfactant-coated spun yarns may bring adverse effects on the cleanness of liquid, such as foaming of the liquid, and increase in TOC (total organic carbon), COD (chemical oxygen demand) and the electric conductivity. In addition, a spun yarn is produced by spinning short fibers as already mentioned, for which at least two steps of forming and

spinning short fibers are required. Thus, use of the spun yarn will sometimes increase a price of the product.

A performance of a non-woven fabric-laminated type filter cartridge depends on the non-woven fabric used. A non-woven fabric is produced mostly by a method in which short fibers are confounded by means of a carding machine or an air laid machine and then subjecting them, if necessary, to heat treatment by means of a hot-air heater or a heating roll, or a method in which a non-woven fabric is directly prepared, such as a melt blowing method and a spun bonding method. However, any machines used for producing non-woven fabrics, such as a carding machine, an air laid machine, a hot-air heater, a heating roll, a melt blowing machine and a spun bonding machine, may cause, for example, uneven basis weights of a non-woven fabric in a lateral direction of a machine. Accordingly, a filter cartridge of poor quality will be produced. Also, use of a more advanced manufacturing technique to avoid such unevenness sometimes raises the production cost. Moreover, production of one kind of non-woven fabric-laminated type filter cartridges needs two to six kinds of non-woven fabrics, and different non-woven fabrics are needed depending on the kind of a filter cartridge. Thus, the production cost will increase in some cases.

Several methods have been proposed in order to solve such problems of conventional filter cartridges. For example, Japanese Utility Model Publication No. 6-7767

proposes a filter cartridge in which a filter material obtained by squashing a tape-shaped paper having porosity while twisting, thereby squeezing it to control a diameter thereof to about 3 mm is wound around a porous internal cylinder in a close twill. This method is advantageous in that a winding pitch can be gradually increased from the porous internal cylinder toward the outside. However, the filter material needs to be squashed and squeezed, so that foreign matters are trapped primarily between the winding pitches of the filter material. Accordingly, it is less expected to trap foreign matters by the filter material itself as is the case of a conventional bobbin winder type filter using spun yarns which traps foreign matters by means of fluffs. This blocks the surface of the filter to shorten the filter life or brings about the poor liquid-passing property in a certain case.

JP-A 1-115423 proposes a filter in which strings obtained by slitting a cellulose spun bonded non-woven fabric into strips and passing them through narrow holes to twist them are wound around a bobbin having a lot of drilled pores. It is considered that this method shall make it possible to prepare a filter having a higher mechanical strength and being free of dissolution in water and elution of a binder, as compared with a conventional roll tissue filter prepared by winding tissue paper in a roll form, which is produced from α -cellulose prepared by refining a coniferous pulp.

However, the cellulose spun bonded non-woven fabric used for this filter has a papery form and thus a too high rigidity, so that it is less expected to trap foreign matters by the filter material itself as is the case of a conventional bobbin winder type filter using spun yarns which traps foreign matters by means of fluffs. Further, the cellulose spun bonded non-woven fabric is liable to swell in a liquid due to its papery form. Swelling may bring about various problems such as a decrease in a filter strength, a change in a filtering accuracy, a deterioration in a liquid-passing property, a reduction in a filter life and the like. Adhesion at fiber intersections of the cellulose spun bonded non-woven fabric are mostly conducted by a certain chemical treatment. Such adhesion is often unsatisfactory, causing a change in a filtering accuracy or falling of fiber chips, so that a stable filtering performance is difficult to achieve.

Further, JP-A 4-45810 proposes a filter prepared by winding a slit non-woven fabric comprising composite fibers in which 10% by weight or more of structural fibers is divided ones of 0.5 denier or less on a porous core cylinder to provide the fiber density of 0.18 to 0.30. This method is advantageously used to trap fine particles contained in a liquid by means of fibers having a high fineness. However, in order to divide the composite fibers, a stress needs to be applied using, for example, high-pressure water, and it is difficult to evenly divide the

fibers all over the non-woven fabric by means of high-pressure water processing. If not evenly divided, there occurs a difference in a trapped particle diameter between a well-divided portion and an insufficiently divided portion of the non-woven fabric, and this may lower the filtering accuracy. Further, the stress applied for dividing sometimes lowers a strength of the non-woven fabric, and this may cause reduction of the resulting filter strength and frequent deformation of the filter during use; or possible change of the void ratio of the filter may reduce the liquid-passing property.

Further, the reduced strength of the non-woven fabric makes it difficult to control a tension in winding around a porous core cylinder, and hence the difficulty in exact control of the void rate may arise. Further, a spinning technique required for producing easily divisible fibers and an increased operation cost in producing thereof lead to an increased production cost of the filter. Such a filter would be usable in a certain field such as the pharmaceutical industry and the electronic industry which require a high filtering performance, if the above mentioned problems of the filtering performance are solved. However, such a filter is considered to be difficult to use in cases in which inexpensive filters are requested such as the filtering of swimming pool water and a plating liquid for the plating industry.

An object of the present invention is to provide a cylindrical filter cartridge which is excellent in a liquid-passing property, a filter life and stability of a filtering accuracy.

5 An object of the present invention is to solve the problems described above. It has been found, as a result of investigations, that a cylindrical filter cartridge which is excellent in a liquid-passing property, a filter life and a stability of a filtering accuracy can be obtained by winding a long fiber non-woven fabric comprising thermoplastic
10 fibers on a perforated cylinder in a twill form.

SUMMARY OF THE INVENTION

15 The present inventors have conducted intensive researches and, as a result, found that the problems described above can be solved by a cylindrical filter cartridge, which is prepared by winding a non-woven fabric strip on a perforated cylinder in a twill form, in which the strip is a long fiber non-woven fabric and/or a melt blown
20 non-woven fabric comprising thermoplastic fibers and an airflow amount (air permeability) is specially related to a basis weight; or by specifying a number of winding in producing the filter cartridge. This finding has led to the present invention.

25 The present invention is composed of:

- (1) A filter cartridge which is prepared by winding a non-woven fabric strip comprising a thermoplastic fiber

around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (A):

$$\log_{10} Y < 3.75 - 0.6 (\log_{10} X) \quad (A)$$

wherein X ($\text{cm}^3/\text{cm}^2/\text{sec}$) is an airflow amount of the non-woven fabric strip measured in accordance with JIS L 1096-A (1990), and Y (g/m^2) is a basis weight thereof.

(2) A filter cartridge which is prepared by winding a long fiber non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (B):

$$\log_{10} Y < 3.75 - 0.75 (\log_{10} X) \quad (B)$$

wherein X ($\text{cm}^3/\text{cm}^2/\text{sec}$) is an airflow amount of the non-woven fabric strip measured in accordance with JIS L 1096-A (1990), and Y (g/m^2) is a basis weight thereof.

(3) A filter cartridge which is prepared by winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein in winding in a twill form, a number (W) of winding the non-woven fabric strip from one end to the other end in a longitudinal direction of the perforated cylinder is one to 10 per a length of 250 mm in the perforated cylinder.

(4) The filter cartridge as described in the item (3), wherein when a 2-fold value (2W) of the winding number (W) is represented by a fraction having a denominator of two figures or less which is a non-reducible approximate value, the denominator is 4 to 40.

(5) The filter cartridge as described in any one of the items (1) to (3), wherein at least a part of fiber intersections of the non-woven fabric strip is thermally bonded.

5 (6) The filter cartridge as described in any one of the items (1) to (3), wherein the non-woven fabric strip has a width of 0.5 to 40 cm.

(7) The filter cartridge as described in any one of the items (1) to (3), wherein a product of a width (cm) and a basis weight (g/m^2) of the non-woven fabric strip is 10 to 200.

(8) The filter cartridge as described in any one of the items (1) to (3), wherein the non-woven fabric strip has a thickness of 0.02 to 1.20 mm.

10 (9) The filter cartridge as described in any one of the items (1) to (3), wherein the non-woven fabric strip is thermal compression bonded by means of a heat embossing roll having an embossing area rate of 5 to 25%.

15 (10) The filter cartridge as described in any one of the items (1) to (3), wherein the filter material of the filter cartridge has a void rate of 65 to 85%.

20 (11) The filter cartridge as described in the item (1) or (3), wherein the non-woven fabric strip is of a long fiber non-woven fabric.

25 (12) The filter cartridge as described in the item (11), wherein the long fiber non-woven fabric is produced by a spun bonding method.

(13) The filter cartridge as described in the item (1) or (3), wherein the non-woven fabric strip is of a melt blown non-woven fabric.

(14) The filter cartridge as described in any one of the items (1) to (3), wherein the thermoplastic fiber is a composite fiber comprising a low melting resin and a high melting resin, a difference of the melting points between these resins being 10°C or more.

(15) The filter cartridge as described in any one of the items (1) to (3), wherein the thermoplastic fiber is a fiber formed from at least one thermoplastic resin selected from the group consisting of a polyester resin, a polyamide resin, a polyethylene resin and a polypropylene resin.

(16) A process for producing a filter cartridge, which comprises winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein the non-woven fabric strip satisfies the following equation (A):

$$\log_{10} Y < 3.75 - 0.6 (\log_{10} X) \quad (A)$$

wherein X ($\text{cm}^3/\text{cm}^2/\text{sec}$) is an airflow amount of the non-woven fabric strip measured in accordance with JIS L 1096-A (1990), and Y (g/m^2) is a basis weight thereof.

(17) A process for producing a filter cartridge, which comprises winding a non-woven fabric strip comprising a thermoplastic fiber around a perforated cylinder in a twill form, wherein in winding in a twill form, a number (W) of winding the non-woven fabric strip from one end to the other

end in a longitudinal direction of the perforated cylinder is one to 10 per a length of 250 mm in the perforated cylinder.

5 BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a conceptual diagram of a spun bonded non-woven fabric.

Fig. 2 is a conceptual diagram of a short fiber non-woven fabric.

10 Fig. 3 represents the equation (A) showing a relation of a basis weight to an airflow amount of the non-woven fabric.

Fig. 4 is an illustration of winding a non-woven fabric strip as it is, without processing.

15 Fig. 5 is an illustration of winding a non-woven fabric strip with twisting.

Fig. 6 is an illustration of winding a non-woven fabric strip with traversing.

20 Fig. 7 is an illustration of trapping foreign matters by means of an embossing pattern of a non-woven fabric.

Fig. 8 is a perspective of the filter cartridge according to the present invention.

Explanation of Codes

- 25 1: Long fiber constituting spun bonded non-woven fabric
2: Foreign matters
3: Bobbin

- 4: Perforated cylinder
- 5: Traverse guide
- 6: Non-woven fabric strip or converged matter thereof
- 7: Filter cartridge
- 5 8: Part where strong thermal compression bonding by an embossing pattern is applied.
- 9: Part where only weak thermal compression bonding by deviating from an embossing pattern is applied

10 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

The embodiment of the present invention shall be explained below in detail.

15 The filter cartridge of the present invention is prepared by winding a non-woven fabric strip comprising a thermoplastic fiber on a perforated cylinder in a twill form.

20 In the present invention, the non-woven fabric strip means a non-woven fabric having a narrow width, which is prepared by slitting (cutting) a wide non-woven fabric or produced directly in a narrow width. It is preferable that a wide non-woven fabric is slit in order to obtain the stable quality at low cost. An optimum width and basis weight of a non-woven fabric to be used shall be described later.

25 In the present invention, the thermoplastic fiber means a fiber produced from a thermoplastic resin. All thermoplastic resins capable of being melt-spun can be used

for the thermoplastic resin used in the present invention. Examples include polyethylene resins such as low density polyethylene, high density polyethylene and linear low density polyethylene; polypropylene resins such as
5 polypropylene and copolymerized polypropylene (for example, binary or multi-component copolymers comprising propylene as a primary component with ethylene, butene-1, 4-methylpentene-1 and the like); other polyolefin resins than the above polyethylene and polypropylene resins; polyester resins such as polyethylene terephthalate, polybutylene terephthalate and low melting polyesters copolymerized with addition of isophthalic acid besides terephthalic acid as an acid component; polyamide resins such as nylon 6 and nylon 66; and thermoplastic resins such as polystyrene, polyurethane elastomers, polyester elastomers and
10 polytetrafluoroethylene.

Functional resins can also be used so as to provide a filter cartridge with a biodegradability derived from biodegradable resins such as a lactic acid base
15 polyester. Further, polyolefin resins and polystyrene resins which can be polymerized using metallocene catalysts are preferably used for a filter cartridge, taking advantage of the characteristics of metallocene resins such as improvements in a strength of a non-woven fabric and a
20 chemical resistance, and a reduction in a production energy. Also, those resins may be blended for use in order to control a heat adhesion property and a rigidity of a non-

woven fabric. When a filter cartridge is used for filtering an aqueous solution of room temperature, polyolefin resins such as polypropylene and polyethylene are preferably used from the viewpoints of a chemical resistance and a cost.

5 When used for a solution of a relatively high temperature, polyester resins and polyamide resins are preferred.

These thermoplastic resins can be blended, if necessary, with publicly known additives.

10 The non-woven fabric strip used in the present invention is preferably a long fiber non-woven fabric or a melt blown non-woven fabric, and the resulting filter cartridge reduces a risk that fibers fall off and are mixed in a filtrate when used for filtering.

15 The long fiber non-woven fabric or melt blown non-woven fabric described above can be used separately as a non-woven fabric strip or in the form of a laminated non-woven fabric of the both.

20 In the filter cartridge of the present invention, the melt blown non-woven fabric as the non-woven fabric strip has a higher fineness than that of the long fiber non-woven fabric, and the texture thereof can easily be homogenized. Accordingly, the resulting filter cartridge can be improved in a filtering accuracy.

25 An average fiber diameter of the above melt blown non-woven fabric varies depending on uses of the filter cartridge and kinds of the resin, and is 0.5 to 1000 μm , preferably 1 to 50 μm . If the average fiber diameter is

less than 0.5 μm , it is difficult to produce the non-woven fabric, which may result in a high-cost filter cartridge. On the other hand, the average fiber diameter exceeding 1000 μm expands a distribution of the fiber diameter and deteriorates a texture of the resulting non-woven fabric. Further, the average fiber diameter exceeding 50 μm may allow the adjacent fibers to bond each other by remaining heat, but it makes no difference especially as long as it does not prevent the effects of the present invention.

The non-woven fabric strip used in the present invention is preferably a long fiber non-woven fabric, a melt blown non-woven fabric or a laminated non-woven fabric thereof, in which at least a part of fiber intersections thereof is thermally bonded. Among them, preferred is the long fiber non-woven fabric in which at least a part of fiber intersections thereof is thermally bonded.

In particular, a non-woven fabric obtained by a spun bonding method is preferred as the long fiber non-woven fabric described above. The spun bonding method is a non-woven fabric production technique in which a thermoplastic fiber discharged from a nozzle is sucked and drawn by an air gun, spread on a conveyor and then thermally bonded. The long fiber non-woven fabric comprising thermoplastic fibers produced by the spun bonding method has a fiber direction aligned along a machine direction as shown in Fig. 1, so that a hole constituted by fibers 1 becomes long and narrow, and a maximum size of the passing particle 2 is

rather small. In contrast with this, a non-woven fabric comprising short fibers obtained by a carding method and the like has a fiber direction not fixed as shown in Fig. 2, so that a hole constituted by fibers 1 has a shape close to a circle or a square, and a maximum size of the passing particle 2 is larger than that of a long fiber non-woven fabric produced by the spun bonding method, even the two has the same fiber diameter and void rate.

In the present invention, other fibers than the thermoplastic fiber, for example, cotton, glass fibers and metallic fibers can be used in combination as structural fibers of the non-woven fabric strip as long as they do not impair a filter life, a liquid-passing property and the functions such as preventing matters from falling off the filter cartridge which are characteristics of the present filter cartridge.

In the non-woven fabric strip used for producing the filter cartridge which is the first embodiment of the present invention, an airflow amount X ($\text{cm}^3/\text{cm}^2/\text{sec}$) and a basis weight Y (g/m^2) which are measured by a JIS L 1096-A method satisfy the following equation (A) by bonding the fiber intersections thereof.

$$\log_{10} Y < 3.75 - 0.6 (\log_{10} X) \quad (A)$$

The filter cartridge of the present invention which is prepared by winding the non-woven fabric strip around a perforated cylinder in a twill form exhibits an excellent filtering accuracy.

A relation of the equation (A) is shown in Fig. 3. The equation (A) represents a shaded area in Fig. 3 and exhibits a basis weight range corresponding to the respective airflow amounts of the non-woven fabric strip. When the airflow amount and the basis weight do not have a relation represented by the shaded area, it means that the basis weight is too large, and a rigidity of the non-woven fabric strip becomes too high, so that it is difficult to minutely wind the non-woven fabric strip around the perforated cylinder, and the resulting filter cartridge may have a reduced filtering accuracy.

If the production process of the present invention is a spun bonding process in which a non-woven fabric is prepared directly from a formed fiber, the resulting filter cartridge reduces a risk that the fibers fall off and are mixed in the filtrate when used for filtering. Further, it is relatively low in cost, and therefore, it is preferable.

In the second embodiment of the present invention, the non-woven fabric strip is a long fiber non-woven fabric, and the airflow amount X ($\text{cm}^3/\text{cm}^2/\text{sec}$) and the basis weight Y (g/m^2) satisfy the following equation (B). In such a case, the filter cartridge is excellent in a non-woven fabric strength and a property of preventing the fibers from falling off the filter cartridge, and therefore it exhibits a particularly excellent filtering accuracy.

$$\log_{10} Y < 3.75 - 0.75 (\log_{10} X) \quad (B)$$

Next, a method for winding the non-woven fabric strip around a perforated cylinder shall be explained. One example of the processes is shown in Fig. 4. A winder conventionally used for a bobbin winder type filter cartridge can be used for the winding machine. A perforated cylinder 4 having a diameter of about 10 to 40 mm and a length of 100 to 1000 mm is installed to a bobbin 3 of this winder. A non-woven fabric strip 6 passes through a yarn passage and a hole of a traverse guide 5 of the winder to be converged and wound around the perforated cylinder one to two times. The perforated cylinder may be thermally bonded to an end part of the non-woven fabric strip in order to accurately wind the strip. The yarn passage of the winder is waved in each longitudinal direction in a twill form by means of the traverse guide 5 disposed parallel to the bobbin, so that the non-woven fabric strip is wound around the perforated cylinder in a twill form by rotation of the bobbin, whereby a filter cartridge 7 is produced. A diameter of the hole disposed in the traverse guide 5 varies depending on a basis weight and a width of the non-woven fabric strip used and falls preferably in a range of 3 to 10 mm. If this diameter is less than 3 mm, a friction between the non-woven fabric strip and the hole is increased, so that the winding tension becomes too high. On the other hand, the value larger than 10 mm may not render the converging size of the non-woven fabric stabilized. Various traverse guides having a narrow hole can be used for the

traverse guide 5. For example, those in an almost circular form, an almost elliptical form and an almost flat form can be used. Further, those having an aperture part at one end of a narrow hole can be used as well.

5 The perforated cylinder functions as a core of a filter cartridge, and the material and the form thereof shall not specifically be restricted as long as it has a strength which is endurable to external pressure applied in filtering and the pressure loss is not markedly high. It may be, for example, an injection-molded article obtained by processing polyethylene or polypropylene into a net type cylinder as is the case with a core used for a conventional filter cartridge or ones obtained by processing ceramics and stainless steel in the same manner. Alternatively, other
10 filter cartridges such as a filter cartridge subjected to pleat-folding processing and a filter cartridge of a non-woven fabric-winding type can be used as a perforated cylinder.
15

20 The winding conditions in this case can be set up according to those in producing a conventional bobbin winder type filter cartridge. Initial speed of the bobbin may be set to, for example, 1000 to 2000 rpm, and the feeding speed may be controlled to apply a tension in winding the non-woven fabric. The void rate of the filter cartridge can be
25 changed by the tension in this case.

 On the other hand, this non-woven fabric strip can be twisted and then wound. One embodiment of the production

process is shown in Fig. 5. Also in this case, a winder conventionally used for a bobbin winder type filter cartridge can be used for the winding machine. The non-woven fabric becomes apparently thick by twisting, and therefore a traverse guide 5 has preferably a larger hole diameter than that in the case of Fig. 4. By twisting a non-woven fabric, an apparent void rate of the non-woven fabric can be changed depending on a twisting number per unit length or a twisting strength, so that the filtering accuracy can be controlled. The twisting number in this case falls preferably in a range of 50 to 1000 times per meter of the non-woven fabric strip. If this value is smaller than 50 times, the twisting effect is scarcely obtained. On the other hand, the value larger than 1000 times will provide the filter cartridge produced with a inferior liquid-passing property. Accordingly, both are not preferred.

It is more preferred to converge the non-woven fabric strip by any method and then wind it around a perforated cylinder. Such a method include one in which the non-woven fabric strip may be passed merely through a small hole to be converged or one in which the cross-sectional form of the non-woven fabric strip may be pre-molded by means of a pleat-forming guide and then passed through a small hole to be processed into a pleated matter. Use of the latter method makes it possible to control a ratio of a traversing speed of the traverse guide to a rotating speed

of the bobbin to change the winding pattern, so that filter cartridges having various performances can be produced from the same kind of the non-woven fabric strip.

One embodiment of a production process in which the non-woven fabric is passed merely through a small hole for converging the strip is shown in Fig. 6. Also in this case, a winder conventionally used for a bobbin winder type filter cartridge can be used for the winding machine. In Fig. 6, the hole of a traverse guide 5 turned into a small hole, thereby converging the non-woven fabric strip, but a guide of a small hole may be provided at a yarn passage in front of the traverse guide 5. The diameter of the small hole varies depending on the basis weight and the width of the non-woven fabric used and falls preferably in the range of 3 to 10 mm. If this diameter is smaller than 3 mm, a friction between the non-woven fabric and the small hole is increased, so that the winding tension becomes too high. On the other hand, the value larger than 10 mm may not render the converging size of the non-woven fabric stabilized.

Further, when producing the above non-woven fabric strip-converged matter, granular activated carbon or ion exchange resins may be present as long as they do not damage the effects of the present invention. In this case, in order to fix granular activated carbon or ion exchange resins, they may be bonded by means of a suitable binder either prior to or after converging the non-woven fabric strip or processing it into a pleated matter, or they may be

first added and then thermally bonded to the structural fibers of the non-woven fabric by heating.

The yarn passage of the winder is waved in twill form by means of a traverse cam disposed parallel to the bobbin, so that the non-woven fabric strip is wound around the perforated cylinder while waving in a twill form. The winding conditions in this case can be set up according to those in producing a conventional bobbin winder type filter cartridge. Initial speed of the bobbin may be set to, for example, 1000 to 2000 rpm, and the feeding speed may be controlled to apply a tension in winding the non-woven fabric. The void rate of the filter cartridge can be changed by the tension in this case.

Further, the tension in winding is controlled to make the void rate of an internal layer small, and the void rate of an intermediate layer to an external layer gradually large as the non-woven fabric is wound around. In particular, when the non-woven fabric strip is first formed into the pleated matter and then is wound around the perforated cylinder, there can be provided a filter cartridge having an ideal filtering structure owing to a difference in rough and dense structures formed in the external layer, the intermediate layer and the internal layer in combination with a deep layer-filtering structure formed by the pleats of the pleated matter.

The filtering accuracy can be changed by controlling a ratio of the traversing speed of the traverse

cam to the rotating speed of the bobbin, thereby changing a number (hereinafter referred to as a winding number and represented by W) of winding the non-woven fabric strip around the perforated cylinder from one end to the other end in a longitudinal direction when winding the non-woven fabric strip in a twill form. That is, the winding number means a rotation number of the bobbin 3 while the traverse guide 5 moves from one end to the other end of the perforated cylinder 4 in a longitudinal direction.

Accordingly, a value of W is not necessarily a natural number. The winding number should be very accurate, and therefore, a moving distance of the traverse guide has to be geared to a rotation number of the bobbin so that this value should not get out of order.

In the filter cartridge of the present invention, a winding number W is 1 to 10, preferably 2 to 8 and more preferably 3 to 5 per 250 mm of the perforated cylinder used for the filter cartridge. If this value is less than one, an angle of traversing becomes too large, and therefore the non-woven fabric strip is liable to get out of the perforated cylinder. On the other hand, if this value exceeds 10, an angle of traversing becomes too small, and the non-woven fabric strip is liable to get out of the perforated cylinder also in this case. Further, if the value deviates from the range of 1 to 10, an initial trapped particle diameter becomes extremely large, resulting in an inadequate filter cartridge.

A relation of the winding number to the filtering accuracy is well known in the case of a wound filter in which a spun yarn is used as a filtering material. In a conventional wound filter in which a spun yarn is used, a winding yarn (that is, a spun yarn) generally has a circular cross-sectional form, and a yarn diameter thereof is about 3 mm at the largest. Thus, the winding number and the pitch of the yarn in winding in a twill form can be represented by the following equations (1) and (2):

$$2 \times W = 2 \times W_0 \pm 1/N \quad (1)$$

$$N = T/W_0/P \quad (2)$$

wherein W is a winding number; W_0 is a natural number approximate to the winding number W; N is an ordered number; T is a traverse width; and P is a pitch of the yarn. Among the above variables, W_0 and N are natural numbers, and W, P and T are arbitrary positive numbers. In general, as the pitch of the yarn becomes smaller, the wind filter having a finer accuracy is prepared. This equation can be applied to a yarn other than a spun yarn, for example, a split yarn.

On the other hand, in the filter cartridge of the present invention, the non-woven fabric strip is used as a filter material in place of a spun yarn, and therefore the equations (1) and (2) cannot be applied as they are. The non-woven fabric is converged in winding as described above, so that a thickness of the yarn becomes far large as compared with that of a conventional spun yarn. Accordingly, even if the conditions of the equations (1) and

(2) are satisfied, the yarns themselves are superposed and a filter cartridge having the intended accuracy is not obtained.

As the third embodiment of the present invention, we have found that a filter cartridge, which is prepared by winding a non-woven fabric strip around a perforated cylinder in a twill form, exhibits an excellent filtering performance when a denominator M_n is a specific value the winding number approximated by the following equation (3):

$$2 \times W \doteq X/M_n \quad (3)$$

wherein X/M_n represent a non-reducible fraction, X and M_n are each independently natural numbers, and n represents a maximum figure of the number; for example, M_2 is an integer of 1 to 99.

In the present invention, when a 2-fold value ($2W$) of the winding number (W) is represented by an approximate fraction having a non-reducible denominator of two figures or less, M_2 in the equation (3), i.e., a value of the denominator is 4 to 40, preferably 5 to 20. As the value of M_2 becomes larger, the filter cartridge having a finer texture is prepared. If this value is less than 4, a texture of the resulting filter cartridge is roughened too much, and it is likely that a filter cartridge end face is not smooth. On the other hand, if the value of M_2 exceeds 40, a texture of the filter cartridge becomes too fine, and it is likely that the liquid-passing property is reduced and the filter life is shortened.

In this case, it is important that the value of $2W$ is approximate to a fraction having a denominator of a natural number of two figures or less. For example, when the winding number is 1.893, $2 \times W$ is 3.786. When this 3.786 is approximated to a fraction having a denominator of one figure, it is 3 and $4/5$ (this means a mixed fraction consisting of 3 and four fifths, and the same shall apply unless otherwise described). Accordingly, when the winding number is 1.893, M_1 is 5 which is the denominator of 3 and $4/5$. Similarly, when $2W$ is approximated to a fraction having a denominator of two figures or less, a value thereof is 3 and $11/14$, and therefore M_2 is 14 which is a denominator of 3 and $11/14$. Similarly, when $2W$ is approximated to a fraction having a denominator of three figures or less, it is 3 and $393/500$, and therefore M_3 is 500. Accordingly, in this case, a value of M_2 in the equation (3) is 14 which is the denominator when approximated to a fraction having a denominator of two figures. When $2W$ is approximated to a fraction having a denominator of two figures or less, 3 and $22/28$ and 3 and $33/42$ are also the most approximate values, but these number are reduced to 3 and $11/14$, so that a value of M_2 is 14 in this case.

The value of M_2 described above is varied in a range of 4 to 40, whereby filter cartridges having various accuracies can be prepared even if the same non-woven fabric strip is used. Further, it can also be combined with a

method of varying a width, a basis weight or a fiber diameter of the non-woven fabric strip.

A deep layer-filtering structure of the filter cartridge can further be optimized by winding the non-woven fabric with M_2 set to a specific value until the major diameter becomes a certain degree, and by further winding the non-woven fabric with the value of M_2 changed.

In the filter cartridge of the present invention, the non-woven fabric strip is wound around the perforated cylinder 2 to form a filter cartridge having a major diameter 1.5 to 3 times as large as that of the perforated cylinder. Even when wound in the same winding number, a space between the non-woven fabric strips is varied depending on a major diameter of the perforated cylinder 4. A major diameter of the perforated cylinder 4 is usually decided according to use conditions, and the filtering performance is not controlled by a major diameter of the perforated cylinder 4. If the winding number is the same, as the major diameter of the filter cartridge becomes larger, the particle diameter of the initial particles trapped on the filter cartridge becomes smaller.

A fiber diameter of the long fiber used for the long fiber non-woven fabric described above varies depending on uses of the filter cartridge and kinds of the resin, and it is preferably in a range of 5 to 680 μm . If the fiber diameter exceeds 680 μm , it makes no difference between continuous yarns merely bound into a bundle and the long

fiber non-woven fabric. On the other hand, even if the fiber diameter is less than 5 μm , the resulting long fiber non-woven fabric can be used for a filter cartridge. However, when the long fiber non-woven fabric is a non-woven fabric prepared by a spun bonding method as described above (hereinafter referred to as a spun bonded non-woven fabric), spinning of fibers having a fiber diameter of less than 5 μm by the spun bonding method reduces a production efficiency and is not practical. The fiber diameter is more preferably 9 to 150 μm .

In the filter cartridge of the present invention, a non-woven fabric prepared by laminating a long fiber non-woven fabric and a melt blown non-woven fabric may be used for the non-woven fabric strip. In this case, it can make good use of both advantages of the long fiber non-woven fabric and the melt blown non-woven fabric. A particle-trapping performance of the filter cartridge is influenced a great deal by a fiber diameter of the melt blown non-woven fabric, and this is particularly preferred when preparing the filter cartridge with a high accuracy.

The laminating method shall not specifically be restricted. A fiber aggregate of the melt blown non-woven fabric and that of the long fiber non-woven fabric (long fiber web) may be produced respectively at different steps and then superposed, or alternatively, fibers may be melt-blown directly on the long fiber non-woven fabric or the long fiber web and laminated. Examples of combinations of

the fibers for the laminated non-woven fabric include two layers of melt blown fiber/long fiber, three layers of long fiber/melt blown fiber/long fiber, and three layers of melt blown fiber/melt blown fiber/long fiber which comprise two melt blown fibers having different fiber diameters.

In the present invention, yarns having different cross sections can be used. They can provide a filter cartridge having the same liquid-passing property and a higher accuracy, as compared with the fibers having a circular cross section, because an amount of trapped fine particles increases as a surface area of the filter becomes larger.

In the present invention, the thermoplastic resin used for producing the thermoplastic fiber can be blended with a hydrophilic resin such as polyvinyl alcohol, or a surface of the non-woven fabric strip can be subjected to plasma treating, in order to improve the liquid-passing property when using the filter cartridge for filtering a water-based liquid.

In the present invention, a heat bonding method is preferred as a method for bonding fiber intersections for preparing the non-woven fabric from the thermoplastic fiber. The method includes a thermal compression bonding method by means of an apparatus such as a thermal embossing roll and a heat flat calender roll; and a method using a heat treating machine of a hot blast-circulating type, a heat through-air type, an infrared heater type or a vertical hot blast-

blowing type. Among them, a method using a thermal embossing roll is preferred, because it can elevate a production rate of a non-woven fabric, provides a good productivity and can reduce a cost.

5 As shown in Fig. 7, a non-woven fabric produced by the method using a thermal embossing roll has part 8 where strong thermal compression bonding by an embossing pattern is applied and part 9 where only weak thermal compression bonding by deviating from an embossing pattern is applied. This makes it possible to trap a lot of foreign matters 2 in the part 8, and a part of the foreign matters in the part 9, while the remaining foreign matters can pass through the long fiber non-woven fabric to move to the following layer. Preferred is this deep layer-filtering structure, in which even the inside of the filter is utilized. In this case, an embossing patterned area is preferably from 5 to 25%. Setting the lower limit of this area to 5% can enhance the filtering effect exerted by the part 8 and 9, and setting the upper limit to 25% can control the rigidity of the non-
10
15
20 woven fabric not to become too high. Further, a part of foreign matters are allowed to pass through the non-woven fabric strip.

25 A composite fiber comprising a low melting resin and a high melting resin, wherein the melting point difference is 10°C or more, preferably 15°C or more, is preferred as the fiber constituting the non-woven fabric strip. The melting point difference of 10°C or more

stabilizes a heat adhesion property in the fiber intersections of the non-woven fabric. In the case of a resin having no melting point, the flow-starting temperature is defined as a melting point. Stabilized heat adhesion in the fiber intersections of non-woven fabric strips will allow less particles which have been trapped in the vicinity of the fiber intersections to flow out of filter cartridges, when a filtering pressure and a flow amount of a solution are elevated, and will result in a less deformation of the filter cartridge. Further, even if a substance contained in a filtrate deteriorate the fibers, the stabilized heat adhesion can reduce probability of the fibers falling, and thus it is desirable.

The composite fiber described above may be in any forms such as a parallel type and a sheath-core type, wherein a low-melting resin is present on at least a part of a fiber surface.

A combination of the low melting resin and the high melting resin in the composite fibers shall not specifically be restricted as long as the melting point difference is 10°C or more, preferably 15°C or more, which includes linear low density polyethylene/polypropylene, high density polyethylene/polypropylene, low density polyethylene/polypropylene, copolymer of propylene with other α -olefin/polypropylene, linear low density polyethylene/high density polyethylene, low density polyethylene/high density polyethylene, various

polyethylenes/thermoplastic polyester, polypropylene/
thermoplastic polyester, copolymerized low melting
thermoplastic polyester/thermoplastic polyester, various
polyethylenes/nylon 6, polypropylene/nylon 6, nylon 6/nylon
66 and nylon 6/thermoplastic polyester. Among them, a
combination of linear low density polyethylene/polypropylene
is preferably used, since rigidity and a void rate of the
non-woven fabric strip can readily be controlled during a
step of adhesion of fiber intersections in producing the
non-woven fabric. When a filter cartridge is used for
filtering a solution of a relatively high temperature, a
combination of low melting polyester/polyethylene
terephthalate can suitably be used, the polyester being
prepared by copolymerizing with isophthalic acid.

In the present invention, other fibers than the
thermoplastic fibers may be contained in the non-woven
fabric strip as long as the effect of the present invention
is not damaged. Examples of the fibers other than the
thermoplastic fibers include rayon, cupra, cotton, hemp,
pulp and carbon fiber. The content of the thermoplastic
fiber may preferably be at least 30% by weight, and it can
be 100% by weight. If it is less than 30% by weight, a
strength of the non-woven fabric is reduced when thermally
bonded by a thermal compression bonding method and a
through-air heat treating method, so that the fibers are
liable to fall off and to be mixed in the filtrate while
filtering.

For preparing the non-woven fabric strip used for the filter cartridge of the present invention, a non-woven fabric-producing set-up, for example, a spinning width may be controlled to directly prepare the non-woven fabric strip, but preferably, a wide non-woven fabric is slit into strips.

A width of the non-woven fabric strip used for the filter cartridge of the present invention is preferably 0.5 to 40 cm. If this width is less than 0.5 cm, the wide non-woven fabric is likely to be broken when the non-woven fabric is slit into strips, and it is difficult to control a tension in winding around a perforated cylinder in a twill form. Further, when preparing a filter cartridge having the same void rate, the winding time is extended and the productivity is reduced. On the other hand, if the width exceeds 40 cm, a friction in a yarn passage of a winder including a traverse guide may be larger or the converged non-woven fabrics may be irregular in size.

A basis weight of the non-woven fabric strip, i.e., a weight per unit area of the non-woven fabric is preferably 5 to 200 g/m². If the value is smaller than 5 g/m², an amount of the fiber is reduced, resulting in an increased unevenness in the non-woven fabric or a reduced strength of the non-woven fabric, or occasionally difficulty in thermal bonding of the fiber intersections. On the other hand, the value larger than 200 g/m² will render the rigidity of the non-woven fabric too much increased, so that

the fabric is difficult to wind around a perforated cylinder in a twill form at the later stage.

5 An upper limit of a width of the non-woven fabric strip varies depending on the basis weight, and a product of a width (cm) and a basis weight (g/m^2) of the non-woven fabric strip is preferably 10 to $200 \text{ cm} \cdot \text{g/m}^2$. The value larger than 200 will render the rigidity of the non-woven fabric excessively increased, so that winding of the non-woven fabric on a perforated cylinder in a twill form becomes difficult at the later stage. Further, the non-woven fabric becomes too thick in converging, so that it becomes difficult to wind it densely. On the other hand, if the product is less than 10, the non-woven fabric may be cut.

10
15
20
25
30
35
40
45
50
55
60
65
70
75
80
85
90
95
100
105
110
115
120
125
130
135
140
145
150
155
160
165
170
175
180
185
190
195
200
205
210
215
220
225
230
235
240
245
250
255
260
265
270
275
280
285
290
295
300
305
310
315
320
325
330
335
340
345
350
355
360
365
370
375
380
385
390
395
400
405
410
415
420
425
430
435
440
445
450
455
460
465
470
475
480
485
490
495
500
505
510
515
520
525
530
535
540
545
550
555
560
565
570
575
580
585
590
595
600
605
610
615
620
625
630
635
640
645
650
655
660
665
670
675
680
685
690
695
700
705
710
715
720
725
730
735
740
745
750
755
760
765
770
775
780
785
790
795
800
805
810
815
820
825
830
835
840
845
850
855
860
865
870
875
880
885
890
895
900
905
910
915
920
925
930
935
940
945
950
955
960
965
970
975
980
985
990
995
1000
1005
1010
1015
1020
1025
1030
1035
1040
1045
1050
1055
1060
1065
1070
1075
1080
1085
1090
1095
1100
1105
1110
1115
1120
1125
1130
1135
1140
1145
1150
1155
1160
1165
1170
1175
1180
1185
1190
1195
1200
1205
1210
1215
1220
1225
1230
1235
1240
1245
1250
1255
1260
1265
1270
1275
1280
1285
1290
1295
1300
1305
1310
1315
1320
1325
1330
1335
1340
1345
1350
1355
1360
1365
1370
1375
1380
1385
1390
1395
1400
1405
1410
1415
1420
1425
1430
1435
1440
1445
1450
1455
1460
1465
1470
1475
1480
1485
1490
1495
1500
1505
1510
1515
1520
1525
1530
1535
1540
1545
1550
1555
1560
1565
1570
1575
1580
1585
1590
1595
1600
1605
1610
1615
1620
1625
1630
1635
1640
1645
1650
1655
1660
1665
1670
1675
1680
1685
1690
1695
1700
1705
1710
1715
1720
1725
1730
1735
1740
1745
1750
1755
1760
1765
1770
1775
1780
1785
1790
1795
1800
1805
1810
1815
1820
1825
1830
1835
1840
1845
1850
1855
1860
1865
1870
1875
1880
1885
1890
1895
1900
1905
1910
1915
1920
1925
1930
1935
1940
1945
1950
1955
1960
1965
1970
1975
1980
1985
1990
1995
2000
2005
2010
2015
2020
2025
2030
2035
2040
2045
2050
2055
2060
2065
2070
2075
2080
2085
2090
2095
2100
2105
2110
2115
2120
2125
2130
2135
2140
2145
2150
2155
2160
2165
2170
2175
2180
2185
2190
2195
2200
2205
2210
2215
2220
2225
2230
2235
2240
2245
2250
2255
2260
2265
2270
2275
2280
2285
2290
2295
2300
2305
2310
2315
2320
2325
2330
2335
2340
2345
2350
2355
2360
2365
2370
2375
2380
2385
2390
2395
2400
2405
2410
2415
2420
2425
2430
2435
2440
2445
2450
2455
2460
2465
2470
2475
2480
2485
2490
2495
2500
2505
2510
2515
2520
2525
2530
2535
2540
2545
2550
2555
2560
2565
2570
2575
2580
2585
2590
2595
2600
2605
2610
2615
2620
2625
2630
2635
2640
2645
2650
2655
2660
2665
2670
2675
2680
2685
2690
2695
2700
2705
2710
2715
2720
2725
2730
2735
2740
2745
2750
2755
2760
2765
2770
2775
2780
2785
2790
2795
2800
2805
2810
2815
2820
2825
2830
2835
2840
2845
2850
2855
2860
2865
2870
2875
2880
2885
2890
2895
2900
2905
2910
2915
2920
2925
2930
2935
2940
2945
2950
2955
2960
2965
2970
2975
2980
2985
2990
2995
3000
3005
3010
3015
3020
3025
3030
3035
3040
3045
3050
3055
3060
3065
3070
3075
3080
3085
3090
3095
3100
3105
3110
3115
3120
3125
3130
3135
3140
3145
3150
3155
3160
3165
3170
3175
3180
3185
3190
3195
3200
3205
3210
3215
3220
3225
3230
3235
3240
3245
3250
3255
3260
3265
3270
3275
3280
3285
3290
3295
3300
3305
3310
3315
3320
3325
3330
3335
3340
3345
3350
3355
3360
3365
3370
3375
3380
3385
3390
3395
3400
3405
3410
3415
3420
3425
3430
3435
3440
3445
3450
3455
3460
3465
3470
3475
3480
3485
3490
3495
3500
3505
3510
3515
3520
3525
3530
3535
3540
3545
3550
3555
3560
3565
3570
3575
3580
3585
3590
3595
3600
3605
3610
3615
3620
3625
3630
3635
3640
3645
3650
3655
3660
3665
3670
3675
3680
3685
3690
3695
3700
3705
3710
3715
3720
3725
3730
3735
3740
3745
3750
3755
3760
3765
3770
3775
3780
3785
3790
3795
3800
3805
3810
3815
3820
3825
3830
3835
3840
3845
3850
3855
3860
3865
3870
3875
3880
3885
3890
3895
3900
3905
3910
3915
3920
3925
3930
3935
3940
3945
3950
3955
3960
3965
3970
3975
3980
3985
3990
3995
4000
4005
4010
4015
4020
4025
4030
4035
4040
4045
4050
4055
4060
4065
4070
4075
4080
4085
4090
4095
4100
4105
4110
4115
4120
4125
4130
4135
4140
4145
4150
4155
4160
4165
4170
4175
4180
4185
4190
4195
4200
4205
4210
4215
4220
4225
4230
4235
4240
4245
4250
4255
4260
4265
4270
4275
4280
4285
4290
4295
4300
4305
4310
4315
4320
4325
4330
4335
4340
4345
4350
4355
4360
4365
4370
4375
4380
4385
4390
4395
4400
4405
4410
4415
4420
4425
4430
4435
4440
4445
4450
4455
4460
4465
4470
4475
4480
4485
4490
4495
4500
4505
4510
4515
4520
4525
4530
4535
4540
4545
4550
4555
4560
4565
4570
4575
4580
4585
4590
4595
4600
4605
4610
4615
4620
4625
4630
4635
4640
4645
4650
4655
4660
4665
4670
4675
4680
4685
4690
4695
4700
4705
4710
4715
4720
4725
4730
4735
4740
4745
4750
4755
4760
4765
4770
4775
4780
4785
4790
4795
4800
4805
4810
4815
4820
4825
4830
4835
4840
4845
4850
4855
4860
4865
4870
4875
4880
4885
4890
4895
4900
4905
4910
4915
4920
4925
4930
4935
4940
4945
4950
4955
4960
4965
4970
4975
4980
4985
4990
4995
5000
5005
5010
5015
5020
5025
5030
5035
5040
5045
5050
5055
5060
5065
5070
5075
5080
5085
5090
5095
5100
5105
5110
5115
5120
5125
5130
5135
5140
5145
5150
5155
5160
5165
5170
5175
5180
5185
5190
5195
5200
5205
5210
5215
5220
5225
5230
5235
5240
5245
5250
5255
5260
5265
5270
5275
5280
5285
5290
5295
5300
5305
5310
5315
5320
5325
5330
5335
5340
5345
5350
5355
5360
5365
5370
5375
5380
5385
5390
5395
5400
5405
5410
5415
5420
5425
5430
5435
5440
5445
5450
5455
5460
5465
5470
5475
5480
5485
5490
5495
5500
5505
5510
5515
5520
5525
5530
5535
5540
5545
5550
5555
5560
5565
5570
5575
5580
5585
5590
5595
5600
5605
5610
5615
5620
5625
5630
5635
5640
5645
5650
5655
5660
5665
5670
5675
5680
5685
5690
5695
5700
5705
5710
5715
5720
5725
5730
5735
5740
5745
5750
5755
5760
5765
5770
5775
5780
5785
5790
5795
5800
5805
5810
5815
5820
5825
5830
5835
5840
5845
5850
5855
5860
5865
5870
5875
5880
5885
5890
5895
5900
5905
5910
5915
5920
5925
5930
5935
5940
5945
5950
5955
5960
5965
5970
5975
5980
5985
5990
5995
6000
6005
6010
6015
6020
6025
6030
6035
6040
6045
6050
6055
6060
6065
6070
6075
6080
6085
6090
6095
6100
6105
6110
6115
6120
6125
6130
6135
6140
6145
6150
6155
6160
6165
6170
6175
6180
6185
6190
6195
6200
6205
6210
6215
6220
6225
6230
6235
6240
6245
6250
6255
6260
6265
6270
6275
6280
6285
6290
6295
6300
6305
6310
6315
6320
6325
6330
6335
6340
6345
6350
6355
6360
6365
6370
6375
6380
6385
6390
6395
6400
6405
6410
6415
6420
6425
6430
6435
6440
6445
6450
6455
6460
6465
6470
6475
6480
6485
6490
6495
6500
6505
6510
6515
6520
6525
6530
6535
6540
6545
6550
6555
6560
6565
6570
6575
6580
6585
6590
6595
6600
6605
6610
6615
6620
6625
6630
6635
6640
6645
6650
6655
6660
6665
6670
6675
6680
6685
6690
6695
6700
6705
6710
6715
6720
6725
6730
6735
6740
6745
6750
6755
6760
6765
6770
6775
6780
6785
6790
6795
6800
6805
6810
6815
6820
6825
6830
6835
6840
6845
6850
6855
6860
6865
6870
6875
6880
6885
6890
6895
6900
6905
6910
6915
6920
6925
6930
6935
6940
6945
6950
6955
6960
6965
6970
6975
6980
6985
6990
6995
7000
7005
7010
7015
7020
7025
7030
7035
7040
7045
7050
7055
7060
7065
7070
7075
7080
7085
7090
7095
7100
7105
7110
7115
7120
7125
7130
7135
7140
7145
7150
7155
7160
7165
7170
7175
7180
7185
7190
7195
7200
7205
7210
7215
7220
7225
7230
7235
7240
7245
7250
7255
7260
7265
7270
7275
7280
7285
7290
7295
7300
7305
7310
7315
7320
7325
7330
7335
7340
7345
7350
7355
7360
7365
7370
7375
7380
7385
7390
7395
7400
7405
7410
7415
7420
7425
7430
7435
7440
7445
7450
7455
7460
7465
7470
7475
7480
7485
7490
7495
7500
7505
7510
7515
7520
7525
7530
7535
7540
7545
7550
7555
7560
7565
7570
7575
7580
7585
7590
7595
7600
7605
7610
7615
7620
7625
7630
7635
7640
7645
7650
7655
7660
7665
7670
7675
7680
7685
7690
7695
7700
7705
7710
7715
7720
7725
7730
7735
7740
7745
7750
7755
7760
7765
7770
7775
7780
7785
7790
7795
7800
7805
7810
7815
7820
7825
7830
7835
7840
7845
7850
7855
7860
7865
7870
7875
7880
7885
7890
7895
7900
7905
7910
7915
7920
7925
7930
7935
7940
7945
7950
7955
7960
7965
7970
7975
7980
7985
7990
7995
8000
8005
8010
8015
8020
8025
8030
8035
8040
8045
8050
8055
8060
8065
8070
8075
8080
8085
8090
8095
8100
8105
8110
8115
8120
8125
8130
8135
8140
8145
8150
8155
8160
8165
8170
8175
8180
8185
8190
8195
8200
8205
8210
8215
8220
8225
8230
8235
8240
8245
8250
8255
8260
8265
8270
8275
8280
8285
8290
8295
8300
8305
8310
8315
8320
8325
8330
8335
8340
8345
8350
8355
8360
8365
8370
8375
8380
8385
8390
8395
8400
8405
8410
8415
8420
8425
8430
8435
8440
8445
8450
8455
8460
8465
8470
8475
8480
8485
8490
8495
8500
8505
8510
8515
8520
8525
8530
8535
8540
8545
8550
8555
8560
8565
8570
8575
8580
8585
8590
8595
8600
8605
8610
8615
8620
8625
8630
8635
8640
8645
8650
8655
8660
8665
8670
8675
8680
8685
8690
8695
8700
8705
8710
8715
8720
8725
8730
8735
8740
8745
8750
8755
8760
8765
8770
8775
8780
8785
8790
8795
8800
8805
8810
8815
8820
8825
8830
8835
8840
8845
8850
8855
8860
8865
8870
8875
8880
8885
8890
8895
8900
8905
8910
8915
8920
8925
8930
8935
8940
8945
8950
8955
8960
8965
8970
8975
8980
8985
8990
8995
9000
9005
9010
9015
9020
9025
9030
9035
9040
9045
9050
9055
9060
9065
9070
9075
9080
9085
9090
9095
9100
9105
9110
9115
9120
9125
9130
9135
9140
9145
9150
9155
9160
9165
9170
9175
9180
9185
9190
9195
9200
9205
9210
9215
9220
9225
9230
9235
9240
9245
9250
9255
9260
9265
9270
9275
9280
9285
9290
9295
9300
9305
9310
9315
9320
9325
9330
9335
9340
9345
9350
9355
9360
9365
9370
9375
9380
9385
9390
9395
9400
9405
9410
9415
9420
9425
9430
9435
9440
9445
9450
9455
9460
9465
9470
9475
9480
9485
9490
9495
9500
9505
9510
9515
9520
9525
9530
9535
9540
9545
9550
9555
9560
9565
9570
9575
9580
9585
9590
9595
9600
9605
9610
9615
9620
9625
9630
9635
9640
9645
9650
9655
9660
9665
9670
9675
9680
9685
9690
9695
9700
9705
9710
9715
9720
9725
9730
9735
9740
9745
9750
9755
9760
9765
9770
9775
9780
9785
9790
9795
9800
9805
9810
9815
9820
9825
9830
9835
9840
9845
9850
9855
9860
9865
9870
9875
9880
9885
9890
9895
9900
9905
9910
9915
9920
9925
9930
9935
9940
9945
9950
9955
9960
9965
9970
9975
9980
9985
9990
9995
10000
10005
10010
10015
10020
10025
10030
10035
10040
10045
10050
10055
10060
10065
10070
10075
10080
10085
10090
10095
10100
10105
10110
10115
10120
10125
10130
10135
10140
10145
10150
10155
10160
10165
10170
10175
10180
10185
10190
10195
10

too high, so that the non-woven fabric is difficult to be wound around a perforated cylinder densely in a twill form.

The non-woven fabric strip is wound and processed into a form of a filter cartridge by the method mentioned above. This may be used for a filter cartridge as it is, or a gasket of foamed polyethylene having a thickness of approx. 3 mm may be stuck on an end surface of the filter cartridge to improve an adhesion property to housing.

In the filter cartridge of the present invention, divided fibers can also be used for the fibers of the non-woven fabric strip. However, since it is actually difficult to evenly divide fibers into divided fibers, a melt blown non-woven fabric having a similar average fiber diameter is more preferably used as described above.

When the non-woven fabric strip is made hydrophilic by incorporating a hydrophilic resin such as polyvinyl alcohol into a raw material resin for the fabric or subjecting the surface thereof to plasma treatment, the liquid-passing property of the resulting filter cartridge can be enhanced in case of filtering an aqueous solution. Accordingly, a filter cartridge using such resin is preferred for filtering an aqueous solution.

In the present invention, the filter cartridge thus prepared has a void rate preferably in a range of 65 to 85%. The value smaller than 65% will render the fiber density too high, so that the liquid-passing property is reduced. On the contrary, the value larger than 85% will

render the strength of the filter cartridge reduced and often cause deformation of the filter cartridge unfavorably when a high filtering pressure is applied.

The liquid-passing property can be improved by providing the non-woven fabric strip with notch or by perforating it. In this case, the number of the notch is preferably 5 to 100 per 10 cm of the non-woven fabric, and the perforation area is preferably 10 to 80%. The filtering performance can be controlled by winding plural non-woven fabric strips, or winding it together with other yarns such as a spun yarn. A wide non-woven fabric may be wound in a layer form while winding the non-woven fabric strip in a traversing manner, whereby the maximum flow-out diameter of particles can be controlled when a filter cartridge having a rough accuracy is prepared.

The filter life can be improved by winding a non-woven fabric having a high fineness in an internal layer of the filter cartridge and then winding a non-woven fabric having a low fineness in an external layer thereof. In this case, a fineness of the external layer is set suitably 2 to 8 times as low as that of the internal layer. Further, the filter life can be improved as well by winding a non-woven fabric having a wide slit width for the internal layer and winding a non-woven fabric having a narrow slit width for the external layer. In this case, a non-woven fabric strip width of the internal layer is set suitably 1.5 to 10 times as large as that of the external layer. Other methods for

improving the filter life include a method of winding a non-woven fabric having a large basis weight for the internal layer and then winding a non-woven fabric having a small basis weight for the external layer, and a method of winding a weakly twisted non-woven fabric for the internal layer and then winding a strongly twisted non-woven fabric for the external layer. It is suitable to set a basis weight of the non-woven fabric in the internal layer 2 to 10 times as large as that of the external layer and to set a twist of the non-woven fabric in the external layer 2 to 10 times as much as that of the internal layer. A dense and rough structure of the filter cartridge can be formed by these methods, and a filter life of the filter cartridge is improved.

In the present invention, an end face of the filter cartridge may preferably be smoothened by heat adhesion, which forms smooth end-sealing parts at both ends of the filter cartridge and elevates the sealing property. The non-woven fabric strip constituting both end parts of the filter cartridge is molten by heat, a solvent, a supersonic wave, etc. and then solidified while forming the smooth end faces. Since the non-woven fabric strip comprising the thermoplastic fiber is used in the present invention, a heating method is preferred.

Examples

The present invention shall be explained below in detail with reference to examples and comparative examples, but the present invention shall not be restricted to these examples. In the respective examples, the physical properties and the filtering performances of the filters were evaluated by the methods described below.

Winder and winding number

A winder had a traverse width (width of traversing) of 250 mm, in which a hole of a traverse guide shown in Fig. 6 had a diameter of 5 mm. An initial speed of a bobbin was set up to 1500 rpm. A winding number (W), that is, a number of winding the non-woven fabric strip around a perforated cylinder from one end to the other end was controlled by interlocking a reciprocating motion of the traverse guide with a rotary motion of the perforated cylinder by means of several gears having an appropriate number of gear teeth.

Basis weight and thickness of non-woven fabric

The non-woven fabric having the area of 625 cm² (Examples 1 to 15 and Comparative Examples 1 to 5) or 500 cm² (Examples 16 to 25 and Comparative Examples 6 to 9) was cut off and weighed. The weight was converted to a weight per square meter to define a basis weight. Further, the thickness of the cut non-woven fabric was measured optionally at 10 points, (Examples 1 to 15 and Comparative Examples 1 to 5) or 12 points (Examples 16 to 25 and Comparative Examples 6 to 9), and the values of 8 points

(Examples 1 to 15 and Comparative Examples 1 to 5) or 10 points (Examples 16 to 25 and Comparative Examples 6 to 9) excluding the maximum value and the minimum value were averaged to define the thickness of the non-woven fabric.

5 The thickness at the respective points was measured on the conditions of a load of 196 Pa and a measuring speed of 2 mm/sec by means of "Digithickness Tester (trade name)" manufactured by Toyo Seiki Seisaku-Sho, Ltd.

Fiber diameter of fiber constituting non-woven fabric

10 The non-woven fabric was sampled at 5 spots at random, and they were photographed through a scanning type electron microscope. 20 fibers per spot were selected at random to measure the diameters of the fibers, and an average value thereof was defined as the fiber diameter (μm) of the non-woven fabric.

Airflow amount

Measured according to JIS L 1096-A (1990) method. When the airflow amount exceeded $790 \text{ cm}^3/\text{cm}^2/\text{sec}$, a measured area of the test sample was reduced.

20 Void rate of filter material for filter cartridge

The major diameter, the minor diameter, the length and the weight of the filter cartridge were measured to determine the void rate using the following equation. In order to determine the void rate of the filter material itself excluding a perforated cylinder, the major diameter of the perforated cylinder was used for the value of the minor diameter, and a value obtained by deducting the weight

25

of the perforated cylinder from the weight of the filter cartridge was used for the value of the weight:

$$\begin{aligned} & (\text{Apparent volume of filter material}) = \{(\text{Major diameter} \\ & \text{of filter material})^2 - (\text{Minor diameter of filter} \\ & \text{material})^2\} / 4 \times \pi \times (\text{Length of filter material}); \\ & (\text{Real volume of filter material}) = (\text{Weight of filter} \\ & \text{material}) / (\text{Density of raw material of filter material}); \\ & (\text{Void rate of filter material}) = \{1 - (\text{Real volume of} \\ & \text{filter material}) / (\text{Apparent volume of filter material})\} \\ & \times 100 (\%). \end{aligned}$$

Initial trapped particle diameter, initial pressure loss and filter life

One filter cartridge was mounted to a housing of a circulating type testing machine for filtering performance, and water was passed to circulate, controlling a flow rate to 30 dm³/minute by means of a pump. A difference in pressures at the inlet and outlet of the filter cartridge was set as an initial pressure loss. Next, a cake prepared by mixing 8 kinds of testing powder I prescribed in JIS Z 8901 (1995) (abbreviated as JIS 8 kinds; intermediate diameter: 6.6. to 8.6 μm) with 7 kinds of the same powder (abbreviated as JIS 7 kinds; intermediate diameter: 27 to 31 μm) in a weight ratio of 1:1 was continuously added at 0.4 g/minute, (Examples 1 to 15 and Comparative Examples 1 to 5), or the JIS 7 kinds were continuously added at 0.2 g/minute (Examples 16 to 25 and Comparative Examples 6 to 9), and the original solution and the filtrate were sampled

5 minutes after starting of the addition. They were diluted to appropriate concentrations, and then the numbers of particles contained in the respective solutions were measured by means of a light shielding type particle detector to calculate an initial trapping efficiency. Further, the value thereof was interpolated to determine a particle diameter showing a trapping efficiency of 80%. The addition of the cake was still continued until the pressure loss of the filter cartridge reached to 0.2 MPa, and the original solution and the filtrate were again sampled to determine a trapped particle diameter. Time consumed from starting addition of the cake until reaching to 0.2 MPa was defined as a filter life. When the pressure difference did not reach to 0.2 MPa even the filter life reached to 1000 minutes, the measurement was discontinued at that point of time.

Bubbling and fiber falling of initial filtrate

One filter cartridge was mounted to a housing of a circulating type testing machine for filtering performance, and ion-exchanged water was passed, controlling a flow rate to 10000 cm³/minute by means of a pump. 1000 cm³ of an initial filtrate was sampled, and 25 cm³ thereof was taken into a colorimetric bottle and stirred vigorously to observe bubbling 10 seconds after stopping the stirring. When a volume of bubble (volume from a liquid surface up to the top of bubble) was 10 cm³ or more, it was judged poor and shown by a symbol "C"; when a volume of bubble was less than 10

cm³, it was judged fair and shown by a symbol "B"; and when less than 5 bubbles having a diameter of 1 mm or more were observed, it was judged good and shown by a symbol "A". Further, 500 cm³ of the initial filtrate was passed through a nitrocellulose filter having a pore diameter of 0.8 μm to judge fiber falling. When the number of fibers having a length of 1 mm or more per cm² of the filter paper were 4 or more, it was judged poor and shown by "C"; the number of 1 to 3 was judged fair and was shown by "B"; and the number of 0 was judged good and shown by "A".

Deformation of filter cartridge

One filter cartridge was mounted to a housing (transparent) of a circulating type testing machine for filtering performance, and water was passed to circulate, controlling a flow rate to 30 dm³/minute by means of a pump. An appearance of the filter cartridge was photographed. The JIS 7 kinds were added until the pressure loss before and after the housing reached 0.5 MPa. Then, an appearance of the filter cartridge was photographed on the same conditions (object distance, magnification, etc.) when the pressure loss before and after the housing reached 0.5 MPa. The major diameter of the filter cartridges shown in the two photographs was measured by image analysis to determine a shrinkage percentage. A shrinkage less than 10% was judged good and shown by "A"; a shrinkage 10% or more and less than 20% was judged fair and shown by "B" and a shrinkage 20% or more was judged poor and shown by "C".

Example 1

Used as a non-woven fabric was a polypropylene melt blown non-woven fabric having a basis weight of 50 g/m², a thickness of 0.8 mm and a fiber diameter of 82 μm, in which fiber intersections were thermally bonded by remaining heat of spinning and an airflow amount was 1400 cm³/cm²/sec. Used for a perforated cylinder was a polypropylene injection-molded article having a minor diameter of 30 mm, a major diameter of 34 mm and a length of 250 mm, and also having 180 holes of 6 mm square. The above melt blown non-woven fabric was slit to a width of 2.5 cm to obtain a non-woven fabric strip. The strip was passed through a traverse hole of the winder to be converged and wound around the perforated cylinder with a winding number set to 4.429 until the major diameter reached to 62 mm to obtain a cylindrical filter cartridge 7 as shown in Fig. 8.

Example 2

A cylindrical filter cartridge was obtained in the same manner as in Example 1, except that used as a non-woven fabric was a polypropylene melt blown non-woven fabric having a basis weight of 20 g/m², a thickness of 0.2 mm and a fiber diameter of 3 μm, in which fiber intersections were thermally bonded by remaining heat of spinning and an airflow amount was 38 cm³/cm²/sec. This filter cartridge had a higher filtering accuracy than that of the filter cartridge described in Example 1.

Example 3

Used as a non-woven fabric were the same polypropylene melt blown non-woven fabric as in Example 2 and a polypropylene spun bonded long fiber non-woven fabric having a basis weight of 20 g/m², a thickness of 0.2 mm, a fiber diameter of 18 μm and an airflow amount of 560 cm³/cm²/sec. One melt blown non-woven fabric and one spun bonded long fiber non-woven fabric each described above were superposed and the fiber intersections were thermal compression bonded by means of a heat embossing roll at a heat bonded area rate of 13% to prepare a laminated non-woven fabric. A cylindrical filter cartridge was obtained in the same manner as in Example 1, except that this non-woven fabric was used to prepare a non-woven fabric strip having a width of 5 cm. This filter cartridge had almost the same filtering accuracy and an excellent filter life as compared with the filter cartridge described in Example 2.

Example 4

Used as a non-woven fabric was a polypropylene spun bonded long fiber non-woven fabric having a basis weight of 20 g/m², a thickness of 0.19 mm and a fiber diameter of 18 μm, in which fiber intersections were thermal compression bonded by means of a heat embossing roll at a heat bonded area rate of 13% and an airflow amount was 490 cm³/cm²/sec. The same perforated cylinder as in Example 1 was used. The spun bonded long fiber non-woven fabric was slit to a width of 5 cm to obtain a non-woven fabric strip. The strip was not converged and wound around the perforated

cylinder by means of a winder with a winding number set to 4.429 until the major diameter reached to 62 mm to obtain a cylindrical filter cartridge.

Example 5

5 The same non-woven fabric strip and perforated cylinder as in Example 1 were used. The non-woven fabric strip was passed through a traverse hole of a winder and converged. It was wound around the perforated cylinder on the same conditions as in Example 4 to obtain a filter cartridge. This filter cartridge had a lower filtering accuracy, a better liquid-passing property and a longer filter life than those of the filter cartridge described in Example 4.

Example 6

10 A cylindrical filter cartridge was obtained in the same manner as in Example 5, except for changing the raw material resin of the spun bonded long fiber non-woven fabric to polyethylene terephthalate. This filter cartridge showed almost the same filtering performance as that of the filter cartridge described in Example 5.

Example 7

15 A cylindrical filter cartridge was obtained in the same manner as in Example 5, except for changing the raw material resin of the spun bonded long fiber non-woven fabric to nylon 66. This filter cartridge showed almost the same filtering performance as that of the filter cartridge described in Example 5.

Example 8

A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that sheath-core type composite fibers comprising high density polyethylene as a low melting component and polypropylene as a high melting component in a weight ratio of 5:5 were used as the structural fibers for the spun bonded long fiber non-woven fabric. This filter cartridge had a more excellent accuracy than that of the filter cartridge described in Example 5 and showed such an excellent stability in the filtering accuracy that the trapped particle diameter at 0.2 MPa scarcely changed from the initial trapped particle diameter.

Example 9

A cylindrical filter cartridge was obtained in the same manner as in Example 8, except that linear low density polyethylene was used as the low melting component for the sheath-core type composite fiber. This filter cartridge had almost the same filtering accuracy as that of the filter cartridge obtained in Example 8 and had a more excellent liquid-passing property than that of the filter cartridge described in Example 8.

Example 10

A cylindrical filter cartridge was obtained in the same manner as in Example 9, except that the thermal bonding method for the fiber intersections was changed from the thermal compression bonding method by a hot embossing roll to a heat treating method by a hot blast-circulating type

heating apparatus. This filter cartridge had a little lower filtering accuracy than that of the filter cartridge described in Example 9.

Example 11

5 A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that the long fiber non-woven fabric was slit to a width of 1 cm and that the winding number was changed to 3.476. This filter cartridge showed almost the same performance as that of the filter cartridge described in Example 5. However, time required for winding was longer than in Example 2.

Example 12

10 A cylindrical filter cartridge was obtained in the same manner as in Example 11, except that the long fiber non-woven fabric was slit to a width of 9 cm and that the winding number was changed to 3.714. This filter cartridge had a lower filtering accuracy than that of the filter cartridge described in Example 11, and this may be because the non-woven fabric strip-converged matter became extremely
15 thick.

20 Example 13

25 A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that a fiber diameter of the fiber constituting the non-woven fabric strip was changed to 40 μm . This filter cartridge had a lower filtering accuracy than that of the filter cartridge described in Example 5.

Example 14

A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that a basis weight of the non-woven fabric strip was changed to 44 g/m². This filter cartridge had a lower filtering accuracy than that of the filter cartridge described in Example 5.

Example 15

A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that the non-woven fabric strip was twisted 100 times per one meter instead of converging. This filter cartridge showed almost the same filtering performance as that of the filter cartridge described in Example 12.

Comparative Example 1

A cylindrical filter cartridge was obtained in the same manner as in Example 2, except that polypropylene spun yarns having a diameter of 2 mm prepared by spinning fibers having a fiber diameter of 22 μ m was used in place of the non-woven fabric strip. This filter cartridge had an initial trapped particle diameter larger than that of the filter cartridge described in Example 5 and almost the same as that of the filter cartridge described in Example 12. However, it had an inferior liquid-passing property and a shorter filter life than those of the filter cartridge described in Example 12. Further, bubbling was observed in the initial filtrate, and falling of the filter material was observed as well.

Comparative Example 2

A cylindrical filter cartridge was obtained in the same manner as in Example 2, except that a filter paper No. 1 prescribed in JIS P 3801 (1995), which was cut to a width of 5 cm, was used in place of the non-woven fabric strip. This filter cartridge had an initial trapped particle diameter smaller than that of the filter cartridge described in Example 5, but the trapped particle diameter at an elevated pressure was changed from the initial one to a large extent. Further, the filter life was extremely short, and falling of the filter material was observed in the initial filtrate.

Comparative Example 3

Short fibers comprising polypropylene and high density polyethylene which were dividable to eight parts and had a fiber diameter of 25 μm were webbed by means of a carding machine, and the webbed matter was subjected to fiber division and fiber entanglement by high pressure water processing to obtain a divided short fiber non-woven fabric having a basis weight of 22 g/m^2 . This non-woven fabric was observed under an electron microscope to carry out image analysis, which showed that 50% by weight of the whole fibers was divided into a fiber diameter of 9 μm . A cylindrical filter cartridge was obtained in the same manner as in Example 5, except that this non-woven fabric was cut to a width of 5 cm and used in place of the non-woven fabric strip. An initial trapped particle diameter in this filter

cartridge was smaller than that in the filter cartridge described in Example 5, but a trapped particle diameter at 0.2 MPa was larger. Further, a little bubbling in the initial filtrate was observed as well as falling of the fibers.

Comparative Example 4

A cylindrical filter cartridge was obtained in the same manner as in Example 11, except that used as a non-woven fabric was a polypropylene melt blown non-woven fabric having a basis weight of 100 g/m², a thickness of 1.5 mm and a fiber diameter of 140 μm, in which fiber intersections were thermally bonded by remaining heat of spinning and an airflow amount was 1400 cm³/cm²/sec. It was difficult to wind the non-woven fabric densely around the perforated cylinder so that the filtering accuracy could not be measured.

Comparative Example 5

A cylindrical filter cartridge was obtained in the same manner as in Example 11, except that used as a non-woven fabric was a polypropylene melt blown non-woven fabric having a basis weight of 140 g/m², a thickness of 0.5 mm and a fiber diameter of 90 μm, in which fiber intersections were thermally bonded by remaining heat of spinning and an airflow amount was 600 cm³/cm²/sec. It was difficult to wind the non-woven fabric densely around the perforated cylinder as was the case with Comparative Example 4 so that the filtering accuracy could not be measured.

Comparative Example 6

Used as a non-woven fabric was a polypropylene spun bonded long fiber non-woven fabric having a basis weight of 90 g/m², a thickness of 0.80 mm and a fiber diameter of 80 μm, in which fiber intersections were thermally bonded by a heat embossing roll at a heat bonded area rate of 13% and an airflow amount was 1000 cm³/cm²/sec. This spun bonded long fiber non-woven fabric was slit into a non-woven fabric strip having a width of 5 cm. The same perforated cylinder as in Example 1 was used. The strip was passed through a traverse hole of the winder to be converged and wound around the perforated cylinder with a winding number set to 4.429 until the major diameter reached to 62 mm to obtain a cylindrical filter cartridge as shown in Fig. 8. In this case, neither equation (A) nor equation (B) was satisfied. As compared with the filter cartridge of Example 4 which had such a high filtering accuracy that an initial trapped particle diameter was 7 μm, this filter cartridge had an initial trapped particle diameter of 103 μm, which proved that it could not trap fine particles.

Comparative Example 7

Used as a non-woven fabric was a polypropylene spun bonded long fiber non-woven fabric having a basis weight of 50 g/m², a thickness of 0.86 mm and a fiber diameter of 500 μm, in which fiber intersections were thermally bonded by a heat embossing roll at a heat bonded area rate of 13% and an airflow amount was 3000 cm³/cm²/sec.

This spun bonded long fiber non-woven fabric was slit into a non-woven fabric strip having a width of 5 cm. The same perforated cylinder as in Example 1 was used. The strip was passed through a traverse hole of the winder to be converged and wound around the perforated cylinder with a winding number set to 4.429 until the major diameter reached to 62 mm to obtain a cylindrical filter cartridge as shown in Fig. 8. In this case, neither equation (A) nor equation (B) was satisfied. As compared with the filter cartridge of Example 4 which had such a high filtering accuracy that an initial trapped particle diameter was 7 μm , this filter cartridge had an initial trapped particle diameter of 349 μm , which proved that it could not trap fine particles.

Table 1

	Example			
	1	2	3	4
Non-woven fabric strip	PP	PP	PP	PP
Raw material of fiber ¹	82	3	18 & 3	18
Fiber diameter μm				
Production process	Melt blow	Melt blow	S + M ²	Spun bonding
Method for bonding fiber intersections	Remaining heat	Remaining heat	Embossing	Embossing
Basis weight g/m^2	50	20	40	20
Width cm	2.5	5	5	5
Thickness mm	0.8	0.2	0.35	0.19
Airflow amount $\text{cm}^3/\text{cm}^2/\text{sec}$	1400	38	35	490
Fitness of equation (A)	A	A	A	A
Filter cartridge	Converging	Converging	Converging	Converging
Processing of non-woven fabric				None
Void rate of filter	78	80	81	77
material				
Initial trapped	80	8	8	7
particle diameter				
Initial pressure loss MPa	0.001	0.025	0.025	0.013
Trapped particle	80	9	9	8
diameter in 0.2 MPa				
Filter life min.	>1000	20	30	70
Bubbling	A	A	A	A
Fiber falling	A	A	A	A

*1: Raw material for sheath/core in the case of composite fiber

*2: Lamination of spun bonded non-woven fabric and melt blown non-woven fabric

Table 1 (Cont'd)

	Example				
	6	7	8	9	10
Non-woven fabric strip ¹	PET	Nylon 66	HDPE/PP	LLDPE/PP	LLDPE/PP
Raw material of fiber ¹	15	16	18	18	18
Fiber diameter μm	Spun bonding	Spun bonding	Spun bonding	Spun bonding	Spun bonding
Production process	Embossing	Embossing	Embossing	Embossing	Hot-air
Method for bonding fiber intersections					circulating
Basis weight g/m^2	20	20	20	20	20
Width cm	5	5	5	5	5
Thickness mm	0.27	0.23	0.19	0.19	0.19
Airflow amount $\text{cm}^3/\text{cm}^2/\text{sec}$	600	580	470	470	450
Fitness of equation (A)	A	A	A	A	A
Filter cartridge	Converging	Converging	Converging	Converging	Converging
Processing of non-woven fabric					
Void rate of filter %	81	81	80	80	81
material					
Initial trapped particle diameter μm	13	13	12	12	13
Initial pressure loss MPa	0.002	0.002	0.003	0.002	0.001
Trapped particle diameter in 0.2 MPa μm	14	14	12	12	13
Filter life min.	210	210	220	220	240
Bubbling	A	A	A	A	A
Fiber falling	A	A	A	A	A

*1: Raw material for sheath/core in the case of composite fiber

Table 2

	Example				
	11	12	13	14	15
Non-woven fabric strip	PP	PP	PP	PP	PP
Raw material of fiber ¹	18	18	40	18	18
Fiber diameter μm	Spun bonding	Spun bonding	Spun bonding	Spun bonding	Spun bonding
Production process	Embossing	Embossing	Embossing	Embossing	Embossing
Method for bonding fiber intersections					
Basis weight g/m^2	20	20	20	44	20
Width cm	1	9	5	2.5	5
Thickness mm	0.19	0.19	0.19	0.39	0.19
Airflow amount $\text{cm}^3/\text{cm}^2/\text{sec}$	490	490	780	260	490
Fitness of equation (A)	A	A	A	A	A
Filter cartridge	Converging	Converging	Converging	Converging	Converging
Processing of non-woven fabric					
Void rate of filter $\%$	80	82	82	80	80
Initial trapped material	12	18	30	17	13
particle diameter μm					
Initial pressure loss MPa	0.003	0.003	0.001	0.003	0.003
Trapped particle μm	13	19	30	18	14
diameter in 0.2 MPa min.					
Filter life	210	630	>1000	620	210
Bubbling	A	A	A	A	A
Fiber falling	A	A	A	A	A

*1: Raw material for sheath/core in the case of composite fiber

Table 2 (Cont'd)

	Comparative Example			
	1	2	3	5
Non-woven fabric strip	(Spun yarn)	(Filter paper)	HDPE/PP	PP
Raw material of fiber ¹	PP	Cellulose	9	90
Fiber diameter μm	-	-	(Fiber	Melt blow
Production process	-	-	confounding)	Remaining
Method for bonding fiber	-	-	(High pressure	heat
intersections	-	-	water)	140
Basis weight g/m^2	-	90	22	140
Width cm	-	1.5	5	1
Thickness mm	-	0.2	0.2	1.5
Airflow amount $\text{cm}^3/\text{cm}^2/\text{sec}$	-	-	150	1400
Fitness of equation (A)	-	-	A	C
Filter cartridge				
Processing of non-woven fabric	-	None	None	Converging
Void rate of filter %	76	72	77	-
material				
Initial trapped μm	18	11	10	-
particle diameter				
Initial pressure loss MPa	0.005	0.022	0.010	-
Trapped particle μm	22	20	13	-
diameter in 0.2 MPa				
min.	280	30	80	-
Filter life	C	A	B	-
Bubbling	C	C	C	-
Fiber falling				

*1: Raw material for sheath/core in the case of composite fiber

Example 16

Used as a non-woven fabric was a polypropylene long fiber non-woven fabric obtained by a spun bonding method. The fiber intersections were thermally bonded by a thermal compression bonding method by means of a heat embossing roll. The non-woven fabric had a basis weight of 22 g/m², a thickness of 200 μ m and an average fiber diameter of 17 μ m. The long fiber non-woven fabric was slit to a width of 50 mm to prepare a non-woven fabric strip.

Further, used for a perforated cylinder was a polypropylene injection-molded article having a minor diameter 30 mm, a major diameter of 34 mm and a length of 250 mm, and also having 180 holes of 6 mm square. A winding number (W) of a winder was set up to 3.1875 (M_2 in the equation (3) is 8 in this case). The non-woven fabric strip was passed through a hole of a traverse guide in the winder and converged, and it was wound around the perforated cylinder until a major diameter reached to 60 mm to obtain a cylindrical filter cartridge. Both end faces thereof were welded by heating for 5 seconds by means of a hot plate having a surface temperature of 175°C to obtain a cylindrical filter cartridge as shown in Fig. 8. Neither bubbling nor falling of the filter material was observed and the pressure loss was small, and thus, the filter cartridge was proved excellent.

Examples 17 to 21

Cylindrical filter cartridges were obtained in the same manner using the same non-woven fabric strip and perforated cylinder as in Example 16, except that the winding numbers (W) were set to 3.2778 (Example 17), 3.2917 (Example 18), 3.3847 (Example 19), 3.4118 (Example 20) and 3.1885 (Example 21), respectively. When the 2-fold values (2W) of these winding numbers (W) are approximated to fractions having denominators (M_2) of two figures or less, the denominators are 9, 12, 13, 17 and 61, respectively. As these filter cartridges had larger M_2 , the initial trapped particle diameters became smaller. Accordingly, the value of M_2 correlates with the initial trapped particle diameter. When 2W are approximated to fractions having denominators (M_3) of three figures or less, the initial trapped particle diameter does not decrease in proportion to the denominator (M_3). For example, M_3 is larger in Example 20 than in Example 21, but the initial trapped particle diameter is smaller in Example 21. Thus, it proves that M_3 in the equation (3) does not correlate with the filtering accuracy. The winding number W is smaller in Example 20 than in Example 21, but the initial trapped particle diameter is smaller in Example 21. Thus, it proves that the initial trapped particle diameter does not increase in proportion to the winding number W. The filter described in Example 21 had a relatively large pressure loss and a little poor liquid-passing property as compared with the other filters. Examples 22 and 23

Cylindrical filter cartridges were obtained in the same manner as in Example 19, except that a width of the non-woven fabric strip was changed to 2 cm (Example 22) or 3 cm (Example 23). These filter cartridges had large initial trapped particle diameters as compared with that of the filter cartridge described in Example 19.

Example 24

A cylindrical filter cartridge was obtained in the same manner as in Example 19, except that used as a non-woven fabric strip was a melt blown non-woven fabric having an average fiber diameter of 2 μm , a basis weight of 22 g/m^2 and a width of 5 cm. This filter cartridge had a small initial trapped particle diameter as compared with that of the filter cartridge described in Example 19.

Example 25

A cylindrical filter cartridge was obtained on the same conditions as in Example 19, except that used as a non-woven fabric strip was a laminated non-woven fabric obtained by thermal compression bonding by means of a heat embossing roll, which comprised three kinds of non-woven fabrics: a polypropylene long fiber non-woven fabric having a basis weight of 5 g/m^2 and a fineness of 2 dtex which was obtained by a spun bonding method, a melt blown non-woven fabric having an average fiber diameter of 2 μm , a basis weight of 22 g/m^2 and a width of 5 cm, and a polypropylene long fiber non-woven fabric having a basis weight of 5 g/m^2 and a fineness of 2 dtex which was obtained by the spun bonding

method. This filter cartridge had a small initial trapped particle diameter as compared with that of the filter cartridge described in Example 19.

Comparative Example 8

5 A polypropylene short fiber having a fineness of 2 dtex, a cut length of 51 mm and a crimp number of 14 was formed by conventional melt spinning, and it was spun to obtain a spun yarn. The spun yarn was wound around the same perforated cylinder as in Example 16 with a winding number (W) set to 3.2252 to obtain a filter cartridge. Both end faces thereof were welded by heating for 5 seconds by means of a hot plate having a surface temperature of 175°C to obtain a filter cartridge. This filter cartridge was uneven on the end face and inferior in a sealing property of the end face. The initial trapped particle diameter thereof was in-between of the initial trapped particle diameters in Examples 19 and 20, but it had a larger pressure loss than those of both Examples 19 and 20 and an inferior liquid-passing property. Further, bubbling and the fibers fallen
10 off the filter material were observed in the filtrate, and therefore, it was not preferred as a filter cartridge.

Comparative Example 9

25 A filter cartridge was obtained in the same manner using the same materials as in Example 16, except that the winding number (W) was changed to 0.6538. The wound non-woven fabric strip was liable to come off this filter cartridge, and it was not suited for a filter cartridge.

Comparative Example 10

A filter cartridge was obtained in the same manner using the same materials as in Example 16, except that the winding number (W) was changed to 10.1923. The wound non-woven fabric strip was liable to come off this filter cartridge, and it was not suited for a filter cartridge.

Comparative Example 11

Used as a structural fiber for the non-woven fabric strip were short fibers comprising polypropylene and high density polyethylene which were dividable into eight parts in a fiber cross section and had a fineness of 2 dtex and a fiber length of 64 mm. This dividable short fiber was webbed by processing by means of a carding machine, and the webbed matter was processed by means of a heat embossing roll to prepare a non-woven fabric. The non-woven fabric was treated twice by means of a water jet apparatus to divide the fiber into a divided non-woven fabric having a basis weight of 22 g/m² and a thickness of 210 μm. The non-woven fabric was slit to a width of 50 mm to prepare a non-woven fabric strip. Further, a winding number (W) of a winder was set up to 3.1875 (M_2 in the equation (3) is 8 in this case). The non-woven fabric strip was passed through a hole of a traverse guide in the winder and converged, and it was wound around a perforated cylinder until a major diameter reached to 60 mm to obtain a cylindrical filter cartridge. Both end faces thereof were welded by heating for 5 seconds by means of a hot plate having a surface

temperature of 175°C to obtain a filter cartridge. The filter cartridge thus obtained had a little reduced filtering accuracy as compared with Example 16. A little bubbling and falling of the filter material were observed in the filtrate, and the pressure loss was large. Further, the filter cartridge was liable to be deformed, and it was judged that its use needs a lot of attention in case of the large pressure.

Comparative Example 12

Used as a non-woven fabric was the same polypropylene spun bonded long fiber non-woven fabric as in Example 16. This fabric was slit into a non-woven fabric strip having a width of 5 cm. The same perforated cylinder as in Example 16 was used. The strip was passed through a hole of a traverse guide in the winder to be converged and wound around a perforated cylinder with a winder number set to 0.8077 until a major diameter reached to 62 mm to obtain a cylindrical filter cartridge as shown in Fig. 8. As compared with the filter cartridge of Example 16 having an initial trapped particle diameter of 59 μm , this filter cartridge had an initial trapped particle diameter of 300 μm , which proved that it could not trap fine particles.

Comparative Example 13

Used as a non-woven fabric was the same polypropylene spun bonded long fiber non-woven fabric as in Example 16. This fabric was slit into a non-woven fabric strip having a width of 5 cm. The same perforated cylinder

as in Example 16 was used. The strip was passed through a hole of a traverse guide in the winder to be converged and wound around a perforated cylinder with a winder number set to 10.0381 until a major diameter reached to 62 mm to obtain a cylindrical filter cartridge as shown in Fig. 8. As compared with the cartridge filter of Example 16 having a initial trapped particle diameter of 59 μm , this cartridge filter has a initial trapped particle diameter of 500 μm , which proved that it could not trap fine particles.

10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
66
67
68
69
70
71
72
73
74
75
76
77
78
79
80
81
82
83
84
85
86
87
88
89
90
91
92
93
94
95
96
97
98
99
100
101
102
103
104
105
106
107
108
109
110
111
112
113
114
115
116
117
118
119
120
121
122
123
124
125
126
127
128
129
130
131
132
133
134
135
136
137
138
139
140
141
142
143
144
145
146
147
148
149
150
151
152
153
154
155
156
157
158
159
160
161
162
163
164
165
166
167
168
169
170
171
172
173
174
175
176
177
178
179
180
181
182
183
184
185
186
187
188
189
190
191
192
193
194
195
196
197
198
199
200
201
202
203
204
205
206
207
208
209
210
211
212
213
214
215
216
217
218
219
220
221
222
223
224
225
226
227
228
229
230
231
232
233
234
235
236
237
238
239
240
241
242
243
244
245
246
247
248
249
250
251
252
253
254
255
256
257
258
259
260
261
262
263
264
265
266
267
268
269
270
271
272
273
274
275
276
277
278
279
280
281
282
283
284
285
286
287
288
289
290
291
292
293
294
295
296
297
298
299
300
301
302
303
304
305
306
307
308
309
310
311
312
313
314
315
316
317
318
319
320
321
322
323
324
325
326
327
328
329
330
331
332
333
334
335
336
337
338
339
340
341
342
343
344
345
346
347
348
349
350
351
352
353
354
355
356
357
358
359
360
361
362
363
364
365
366
367
368
369
370
371
372
373
374
375
376
377
378
379
380
381
382
383
384
385
386
387
388
389
390
391
392
393
394
395
396
397
398
399
400
401
402
403
404
405
406
407
408
409
410
411
412
413
414
415
416
417
418
419
420
421
422
423
424
425
426
427
428
429
430
431
432
433
434
435
436
437
438
439
440
441
442
443
444
445
446
447
448
449
450
451
452
453
454
455
456
457
458
459
460
461
462
463
464
465
466
467
468
469
470
471
472
473
474
475
476
477
478
479
480
481
482
483
484
485
486
487
488
489
490
491
492
493
494
495
496
497
498
499
500
501
502
503
504
505
506
507
508
509
510
511
512
513
514
515
516
517
518
519
520
521
522
523
524
525
526
527
528
529
530
531
532
533
534
535
536
537
538
539
540
541
542
543
544
545
546
547
548
549
550
551
552
553
554
555
556
557
558
559
560
561
562
563
564
565
566
567
568
569
570
571
572
573
574
575
576
577
578
579
580
581
582
583
584
585
586
587
588
589
590
591
592
593
594
595
596
597
598
599
600
601
602
603
604
605
606
607
608
609
610
611
612
613
614
615
616
617
618
619
620
621
622
623
624
625
626
627
628
629
630
631
632
633
634
635
636
637
638
639
640
641
642
643
644
645
646
647
648
649
650
651
652
653
654
655
656
657
658
659
660
661
662
663
664
665
666
667
668
669
670
671
672
673
674
675
676
677
678
679
680
681
682
683
684
685
686
687
688
689
690
691
692
693
694
695
696
697
698
699
700
701
702
703
704
705
706
707
708
709
710
711
712
713
714
715
716
717
718
719
720
721
722
723
724
725
726
727
728
729
730
731
732
733
734
735
736
737
738
739
740
741
742
743
744
745
746
747
748
749
750
751
752
753
754
755
756
757
758
759
760
761
762
763
764
765
766
767
768
769
770
771
772
773
774
775
776
777
778
779
780
781
782
783
784
785
786
787
788
789
790
791
792
793
794
795
796
797
798
799
800
801
802
803
804
805
806
807
808
809
810
811
812
813
814
815
816
817
818
819
820
821
822
823
824
825
826
827
828
829
830
831
832
833
834
835
836
837
838
839
840
841
842
843
844
845
846
847
848
849
850
851
852
853
854
855
856
857
858
859
860
861
862
863
864
865
866
867
868
869
870
871
872
873
874
875
876
877
878
879
880
881
882
883
884
885
886
887
888
889
890
891
892
893
894
895
896
897
898
899
900
901
902
903
904
905
906
907
908
909
910
911
912
913
914
915
916
917
918
919
920
921
922
923
924
925
926
927
928
929
930
931
932
933
934
935
936
937
938
939
940
941
942
943
944
945
946
947
948
949
950
951
952
953
954
955
956
957
958
959
960
961
962
963
964
965
966
967
968
969
970
971
972
973
974
975
976
977
978
979
980
981
982
983
984
985
986
987
988
989
990
991
992
993
994
995
996
997
998
999
1000
1001
1002
1003
1004
1005
1006
1007
1008
1009
1010
1011
1012
1013
1014
1015
1016
1017
1018
1019
1020
1021
1022
1023
1024
1025
1026
1027
1028
1029
1030
1031
1032
1033
1034
1035
1036
1037
1038
1039
1040
1041
1042
1043
1044
1045
1046
1047
1048
1049
1050
1051
1052
1053
1054
1055
1056
1057
1058
1059
1060
1061
1062
1063
1064
1065
1066
1067
1068
1069
1070
1071
1072
1073
1074
1075
1076
1077
1078
1079
1080
1081
1082
1083
1084
1085
1086
1087
1088
1089
1090
1091
1092
1093
1094
1095
1096
1097
1098
1099
1100
1101
1102
1103
1104
1105
1106
1107
1108
1109
1110
1111
1112
1113
1114
1115
1116
1117
1118
1119
1120
1121
1122
1123
1124
1125
1126
1127
1128
1129
1130
1131
1132
1133
1134
1135
1136
1137
1138
1139
1140
1141
1142
1143
1144
1145
1146
1147
1148
1149
1150
1151
1152
1153
1154
1155
1156
1157
1158
1159
1160
1161
1162
1163
1164
1165
1166
1167
1168
1169
1170
1171
1172
1173
1174
1175
1176
1177
1178
1179
1180
1181
1182
1183
1184
1185
1186
1187
1188
1189
1190
1191
1192
1193
1194
1195
1196
1197
1198
1199
1200
1201
1202
1203
1204
1205
1206
1207
1208
1209
1210
1211
1212
1213
1214
1215
1216
1217
1218
1219
1220
1221
1222
1223
1224
1225
1226
1227
1228
1229
1230
1231
1232
1233
1234
1235
1236
1237
1238
1239
1240
1241
1242
1243
1244
1245
1246
1247
1248
1249
1250
1251
1252
1253
1254
1255
1256
1257
1258
1259
1260
1261
1262
1263
1264
1265
1266
1267
1268
1269
1270
1271
1272
1273
1274
1275
1276
1277
1278
1279
1280
1281
1282
1283
1284
1285
1286
1287
1288
1289
1290
1291
1292
1293
1294
1295
1296
1297
1298
1299
1300
1301
1302
1303
1304
1305
1306
1307
1308
1309
1310
1311
1312
1313
1314
1315
1316
1317
1318
1319
1320
1321
1322
1323
1324
1325
1326
1327
1328
1329
1330
1331
1332
1333
1334
1335
1336
1337
1338
1339
1340
1341
1342
1343
1344
1345
1346
1347
1348
1349
1350
1351
1352
1353
1354
1355
1356
1357
1358
1359
1360
1361
1362
1363
1364
1365
1366
1367
1368
1369
1370
1371
1372
1373
1374
1375
1376
1377
1378
1379
1380
1381
1382
1383
1384
1385
1386
1387
1388
1389
1390
1391
1392
1393
1394
1395
1396
1397
1398
1399
1400
1401
1402
1403
1404
1405
1406
1407
1408
1409
1410
1411
1412
1413
1414
1415
1416
1417
1418
1419
1420
1421
1422
1423
1424
1425
1426
1427
1428
1429
1430
1431
1432
1433
1434
1435
1436
1437
1438
1439
1440
1441
1442
1443
1444
1445
1446
1447
1448
1449
1450
1451
1452
1453
1454
1455
1456
1457
1458
1459
1460
1461
1462
1463
1464
1465
1466
1467
1468
1469
1470
1471
1472
1473
1474
1475
1476
1477
1478
1479
1480
1481
1482
1483
1484
1485
1486
1487
1488
1489
1490
1491
1492
1493
1494
1495
1496
1497
1498
1499
1500
1501
1502
1503
1504
1505
1506
1507
1508
1509
1510
1511
1512
1513
1514
1515
1516
1517
1518
1519
1520
1521
1522
1523
1524
1525
1526
1527
1528
1529
1530
1531
1532
1533
1534
1535
1536
1537
1538
1539
1540
1541
1542
1543
1544
1545
1546
1547
1548
1549
1550
1551
1552
1553
1554
1555
1556
1557
1558
1559
1560
1561
1562
1563
1564
1565
1566
1567
1568
1569
1570
1571
1572
1573
1574
1575
1576
1577
1578
1579
1580
1581
1582
1583
1584
1585
1586
1587
1588
1589
1590
1591
1592
1593
1594
1595
1596
1597
1598
1599
1600
1601
1602
1603
1604
1605
1606
1607
1608
1609
1610
1611
1612
1613
1614
1615
1616
1617
1618
1619
1620
1621
1622
1623
1624
1625
1626
1627
1628
1629
1630
1631
1632
1633
1634
1635
1636
1637
1638
1639
1640
1641
1642
1643
1644
1645
1646
1647
1648
1649
1650
1651
1652
1653
1654
1655
1656
1657
1658
1659
1660
1661
1662
1663
1664
1665
1666
1667
1668
1669
1670
1671
1672
1673
1674
1675
1676
1677
1678
1679
1680
1681
1682
1683
1684
1685
1686
1687
1688
1689
1690
1691
1692
1693
1694
1695
1696
1697
1698
1699
1700
1701
1702
1703
1704
1705
1706
1707
1708
1709
1710
1711
1712
1713
1714
1715
1716
1717
1718
1719
1720
1721
1722
1723
1724
1725
1726
1727
1728
1729
1730
1731
1732
1733
1734
1735
1736
1737
1738
1739
1740
1741
1742
1743
1744
1745
1746
1747
1748
1749
1750
1751
1752
1753
1754
1755
1756
1757
1758
1759
1760
1761
1762
1763
1764
1765
1766
1767
1768
1769
1770
1771
1772
1773
1774
1775
1776
1777
1778
1779
1780
1781
1782
1783
1784
1785
1786
1787
1788
1789
1790
1791
1792
1793
1794
1795
1796
1797
1798
1799
1800
1801
1802
1803
1804
1805
1806
1807
1808
1809
1810
1811
1812
1813
1814
1815
1816
1817
1818
1819
1820
1821
1822
1823
1824
1825
1826
1827
1828
1829
1830
1831
1832
1833
1834
1835
1836
1837
1838
1839
1840
1841
1842
1843
1844
1845
1846
1847
1848
1849
1850
1851
1852
1853
1854
1855
1856
1857
1858
1859
1860
1861
1862
1863
1864
1865
1866
1867
1868
1869
1870
1871
1872
1873
1874
1875
1876
1877
1878
1879
1880
1881
1882
1883
1884
1885
1886
1887
1888
1889
1890
1891
1892
1893
1894
1895
1896
1897
1898
1899
1900
1901
1902
1903
1904
1905
1906
1907
1908
1909
1910
1911
1912
1913
1914
1915
1916
1917
1918
1919
1920
1921
1922
1923
1924
1925
1926
1927
1928
1929
1930
1931
1932
1933
1934
1935
1936
1937
1938
1939
1940
1941
1942
1943
1944
1945
1946
1947
1948
1949
1950
1951
1952
1953
1954
1955
1956
1957
1958
1959
1960
1961
1962
1963
1964
1965
1966
1967
1968
1969
1970
1971
1972
1973
1974
1975
1976
1977
1978
1979
1980
1981
1982
1983
1984
1985
1986
1987
1988
1989
1990
1991
1992
1993
1994
1995
1996
1997
1998
1999
2000
2001
2002
2003
2004
2005
2006
2007
2008
2009
2010
2011
2012
2013
2014
2015
2016
2017
2018
2019
2020
2021
2022
2023
2024
2025
2026
2027
2028
2029
2030
2031
2032
2033
2034
2035
2036
2037
2038
2039
2040
2041
2042
2043
2044
2045
2046
2047
2048
2049
2050
2051
2052
2053
2054
2055
2056
2057
2058
2059
2060
2061
2062
2063
2064
2065
2066
2067
2068
2069
2070
2071
2072
2073
2074
2075
2076
2077
2078
2079
2080
2081
2082
2083
2084
2085
2086
2087
2088
2089
2090
2091
2092
2093
2094
2095
2096
2097
2098
2099
2100
2101
2102
2103
2104
2105
2106
2107
2108
2109
2110
2111
2112
2113
2114
2115
2116
2117
2118
2119
2120
2121
2122
2123
2124
2125
2126
2127
2128
2129
2130
2131
2132
2133
2134
2135
2136
2137
2138
2139
2140
2141
2142
2143
2144
2145
2146
2147
2148
2149
2150
2151
2152
2153
2154
2155
2156
2157
2158
2159
2160
2161
2162
2163
2164
2165
2166
2167
2168
2169
2170
2171
2172
2173
2174
2175
2176
2177
2178
2179
2180
2181
2182
2183
2184
2185
2186
2187
2188
2189
2190
2191
2192
2193
2194
2195
2196
2197
2198
2199
2200
2201
2202
2203
2204
2205
2206
2207
2208
2209
2210
2211
2212
2213
2214

Table 3

	W	Approximation of 2W with denominator of two figures	M ₂	Approximation of 2W with denominator of three figures	M ₃	Non-woven fabric	Width cm	Basis weight g/cm ²
Example 16	3.1875	6 and 3/8	8	6 and 3/8	8	S	5	22
Example 17	3.2778	6 and 5/9	9	6 and 5/9	9	S	5	22
Example 18	3.2917	6 and 7/12	12	6 and 7/12	12	S	5	15
Example 19	3.3847	6 and 10/13	13	6 and 347/451	451	S	5	22
Example 20	3.4118	6 and 14/17	17	6 and 691/839	839	S	5	22
Example 21	3.1885	6 and 23/61	61	6 and 118/313	313	S	5	22
Example 22	3.3847	6 and 10/13	13	6 and 347/451	451	S	2	22
Example 23	3.3847	6 and 10/13	13	6 and 347/451	451	S	3	22
Example 24	3.3847	6 and 10/13	13	6 and 347/451	451	M	5	22
Example 25	3.3847	6 and 10/13	13	6 and 347/451	451	SMS	5	32
Comparative Example 8	3.2252	6 and 9/20	13	6 and 168/373	373	Spun yarn	0.3	-
Comparative Example 9	0.6538	1 and 4/13	13	1 and 255/829	829	S	5	22
Comparative Example 10	10.1923	20 and 5/13	13	20 and 5/13	13	S	5	22
Comparative Example 11	3.1875	6 and 3/8	8	6 and 3/8	8	Divided yarn	5	22

S : Spun bonded non-woven fabric

M : Melt blown non-woven fabric

SMS: Spun bonded non-woven fabric/melt blown non-woven fabric/spun bonded non-woven fabric

Table 3 (Cont'd)

	Width \times basis weight $\text{cm} \times \text{g/cm}^2$	Void rate %	80% trapped particle diameter μm	Pressure loss MPa	Bubbling	Falling of filter material	Deformation
Example 16	110	85	59	0.003	A	A	A
Example 17	110	82	39	0.004	A	A	A
Example 18	75	76	8.3	0.018	A	A	A
Example 19	110	81	27	0.006	A	A	A
Example 20	110	76	7.5	0.020	A	A	A
Example 21	110	74	5	0.030	A	A	A
Example 22	44	81	28	0.005	A	A	A
Example 23	66	78	17	0.009	A	A	A
Example 24	110	81	20	0.006	A	A	A
Example 25	160	81	20	0.006	A	A	A
Comparative Example 8	-	70	10	0.030	C	C	B
Comparative Example 9	110	-	-	-	-	-	-
Comparative Example 10	110	-	-	-	-	-	-
Comparative Example 11	110	85	50	0.004	B	B	C

Effects of the Invention

The filter cartridge of the present invention has a high filtering accuracy, a long filter life and a good liquid-passing property, in which an initial trapped particle diameter little changes, a pressure loss is small and neither bubbling nor falling of the filter material is observed, as compared with a conventional bobbin winder type filter cartridge.